

# R3PACK



## **R3PACK - REDUCE, REUSE, RETHINK PACKAGING TOWARDS NOVEL FIBRE-BASED PACKAGING AND REUSE SCHEMES**

Grant Agreement No. 101060806

**Work package:** WP6 - Impacts assessment  
**Task:** 6.1 - State of the art packaging LCA  
**Deliverable:** D 6.1 - Part B

**Dissemination level:** Public  
**Issue date:** March 2024  
**Lead beneficiary:** POLIMI



**Funded by  
the European Union**

This project has received funding from the European Union's Horizon Europe Research and Innovation programme under Grant Agreement No 101060806. This document reflects the views of the author(s) and does not necessarily reflect the views or policy of the European Commission. Whilst efforts have been made to ensure the accuracy and completeness of this document, the European Commission shall not be liable for any errors or omissions, however

## DOCUMENT INFORMATION

HISTORY OF CHANGES		
Version	Publication date	Changes
1.0	12.03.2024	Draft to Reset
2.0	30.03.2024	Deliverable

ADDITIONAL AUTHOR(S) CONTRIBUTION	
Name	Organization
Barbara Del Curto, Romina Santi, Carlo Proserpio, Stefano Ferraresi	POLIMI
Daniele Bussini, Chiara Cappelletti	Innovhub

DOCUMENT DISTRIBUTION		
Issue	Date	Distributed to
V1		European Commission

VERIFICATION AND APPROVAL		
	Date	Distributed to



## TABLE OF CONTENT

Acronyms.....	4
Definitions.....	4
<b>1. SUMMARY.....</b>	<b>5</b>
<b>2. GENERAL INFORMATION ABOUT THE PRODUCTS IN SCOPE.....</b>	<b>5</b>
<b>3. GOAL OF THE STUDIES.....</b>	<b>7</b>
<b>4. SCOPE OF THE STUDIES.....</b>	<b>7</b>
4.1. Functional unit and reference flow.....	7
4.2. System boundary.....	8
4.3. Environmental Footprint impact categories.....	9
<b>5. LIFE CYCLE INVENTORY ANALYSIS.....</b>	<b>10</b>
5.1. Data collection and quality.....	10
5.2. LCI organization.....	11
<b>6. IMPACT ASSESSMENT RESULTS.....</b>	<b>24</b>
<b>7. INTERPRETING PEF RESULTS.....</b>	<b>49</b>
7.1. Relevant impact categories.....	49
7.2. Relevant impact categories overview and comments.....	52
<b>8. ANNEXES.....</b>	<b>55</b>
8.1. Annex I: Data collection.....	55
<b>References.....</b>	<b>61</b>



# LCAs Results - State of the Art

## REUSE

### PEF Report

## Acronyms

CFF: Circular Footprint Formula

EF: Environmental Footprint

LCA: Life Cycle Assessment

LCI: Life Cycle Inventory

PEF: Product Environmental Footprint

PEFCRs: Product Environmental Footprint Category Rules

PP+M: PreProduction & Manufacturing

EoL: End-of-life

EF: Environmental Footprint

## Definitions

**Life cycle Assessment (LCA)** – Compilation and evaluation of the inputs, outputs and the potential environmental impacts of a product system throughout its life cycle (ISO 14040:2006).

**Product Environmental Footprint Category Rules (PEFCRs)** – Product category specific, life cycle based rules that complement general methodological guidance for PEF studies by providing further specification at the level of a specific product category. PEFCRs help to shift the focus of the PEF study towards those aspects and parameters that matter the most, and hence contribute to increased relevance, reproducibility and consistency of the results by reducing costs versus a study based on the comprehensive requirements of the PEF method. Only the PEFCRs listed on the European Commission website ([http://ec.europa.eu/environment/eusdd/smgrp/PEFCR\\_OEFSR\\_en.htm](http://ec.europa.eu/environment/eusdd/smgrp/PEFCR_OEFSR_en.htm)) are recognised as in line with this method).



Funded by  
the European Union

This project has received funding from the European Union's Horizon Europe Research and Innovation programme under Grant Agreement No 101060806. This document reflects the views of the author(s) and does not necessarily reflect the views or policy of the European Commission. Whilst efforts have been made to ensure the accuracy and completeness of this document, the European Commission shall not be liable for any errors or omissions, however

## 1. SUMMARY

The goal of the following work is the environmental impact evaluation of the state-of-the-art related to the packaging solutions selected for the reuse within the R3PACK project. The methodology followed is the Life Cycle Assessment (LCA) carried out through SimaPro software and following the PEF method with some adaptations (declared in the report). This report will analyse twelve primary packaging belonging to nine different food categories defined in the R3PACK project. The functional unit is «*one unit of food packaging of a determined capacity able to contain, preserve, protect the food inside and inform about it, guaranteeing proper food safety and shelf life*». The main limitations and assumptions are due to the lack of primary data, replaced by proxy datasets. Since this report aims to show the main impact assessment results, these are limited to highlighting the most relevant life cycle stages, processes, and impact categories. This state-of-the-art analysis will be necessary to set the baseline for comparisons with the newly developed reuse loops in D 6.3 - Part B.



## 2. GENERAL INFORMATION ABOUT THE PRODUCTS IN SCOPE

This second part (B) of D6.1 provides the results of Life Cycle Assessment (LCA) studies related to twelve existing packaging (state of the art) selected for the reuse. The general table below (Tab. 1) shows the relevant information for each product analysed, i.e., product name, format, nominal capacity (in grams or millilitres), reference food product category (among those covered by the R3PACK project), name of the company using the packaging. For all products, the study's publication date coincides with the deadline for the deliverable D6.1 B (M22, March 2024). The geographic validity of the research and the country where the product is consumed/sold is France, Europe.

Each packaging is marked with an identification number (LCA ID) to identify the LCA dedicated to it.

In cases where data relating to several packaging have been provided in the same food category, the one deemed most representative or the one for which more detailed data has been retrieved has been selected.








Tab 1. Products analyzed

	<p><b>Product</b> Florette Shaker Ananas  <b>Format</b> PET Cup  <b>Capacity</b> 400 ml  <b>Food category</b> Prepared fruits  <b>Company</b> Floréale  <b>LCA ID</b> 01</p>
	<p><b>Product</b> Salad MDD  <b>Format</b> PET Tray  <b>Capacity</b> 250 g  <b>Food category</b> Prepared salad  <b>Company</b> LSDH  <b>LCA ID</b> 02</p>





**Funded by  
the European Union**

This project has received funding from the European Union's Horizon Europe Research and Innovation programme under Grant Agreement No 101060806. This document reflects the views of the author(s) and does not necessarily reflect the views or policy of the European Commission. Whilst efforts have been made to ensure the accuracy and completeness of this document, the European Commission shall not be liable for any errors or omissions, however

	<p><b>Product</b> Sour cream  <b>Format</b> PP Cup  <b>Capacity</b> 200 g  <b>Food category</b> Yoghurt  <b>Company</b> Yoplait  <b>LCA ID</b> 03</p>
	<p><b>Product</b> Greek yoghurt  <b>Format</b> PP Cup  <b>Capacity</b> 450 g  <b>Food category</b> Yoghurt  <b>Company</b> Yoplait  <b>LCA ID</b> 04</p>
	<p><b>Product</b> Pork chop  <b>Format</b> EPS Tray  <b>Capacity</b> 500 g  <b>Food category</b> In-shop products  <b>Company</b> (none)  <b>LCA ID</b> 05</p>
	<p><b>Product</b> Grated cheese  <b>Format</b> OPA &amp; LDPE Film  <b>Capacity</b> 180 g  <b>Food category</b> Cheese  <b>Company</b> Sodiaal  <b>LCA ID</b> 08</p>
	<p><b>Product</b> Peanut curl  <b>Format</b> OPP Film  <b>Capacity</b> 125 g  <b>Food category</b> Chips  <b>Company</b> Altho  <b>LCA ID</b> 09</p>
	<p><b>Product</b> Savory biscuits  <b>Format</b> OPP Sachet &amp; Cardboard  <b>Capacity</b> 85- 105 g  <b>Food category</b> Savory biscuits  <b>Company</b> Europe Snacks  <b>LCA ID</b> 10</p>
	<p><b>Product</b> Orange Juice MDD  <b>Format</b> PET clear Bottle  <b>Capacity</b> 1 l  <b>Food category</b> Juice  <b>Company</b> LSDH  <b>LCA ID</b> 11</p>
	<p><b>Product</b> UHT Milk  <b>Format</b> PET Opaque Bottle  <b>Capacity</b> 1 l  <b>Food category</b> Milk  <b>Company</b> LSDH  <b>LCA ID</b> 12</p>



	<p><b>Product</b> UHT Milk</p> <p><b>Format</b> PEHD Bottle</p> <p><b>Capacity</b> 1 l</p> <p><b>Food category</b> Milk</p> <p><b>Company</b> Sodiaal</p> <p><b>LCA ID</b> 13</p>
	<p><b>Product</b> Minis GF Choco</p> <p><b>Format</b> Cardboard box + flowpacks</p> <p><b>Capacity</b> 168 g</p> <p><b>Food category</b> Savory biscuits</p> <p><b>Company</b> Biscuit Bouvard</p> <p><b>LCA ID</b> 14</p>

### 3. GOAL OF THE STUDIES

The following environmental impact analyses aim to evaluate, define and interpret the environmental criticalities deriving from the life cycle of the existing packaging solutions selected for the reuse within the R3PACK project. This second part (Part B), defined in Task 6.1, is intended to provide data on the packaging's state-of-the-art related impacts. These data will be necessary to set comparisons with reusing solutions selected in WP3 and evaluate the actual environmental improvements. The partner contributors to WP3 constitute the target audience of this study, and the commissioner is to be considered R3PACK project.

The impact evaluation will be conducted through Life Cycle Assessment (LCA) defined by standards ISO 14040 and 14044, using the SimaPro software (PRé Sustainability). The impact assessment will be carried out considering datasets and environmental indicators defined in the PEF methodology proposed by European Commission. The standard methods to measure the life cycle environmental performances have been included in the Commission Recommendation 2021/2279 published in December 2021. Environmental Footprint (EF) methods are in a transition phase, and – to date – no PEF CRs are available for packaging products. Some methodological limitations have been applied concerning the established PEF methodology<sup>1</sup>: limitations, assumptions and other non-PEF compliant elements are declared along the report.

### 4. SCOPE OF THE STUDIES

#### 4.1. Functional unit and reference flow

The functional unit<sup>2</sup> of the analysed system is defined as follows: “**one unit of food packaging**” responding to the four following aspects:

- **Function(s)/service(s) provided:** contain, preserve, protect during distribution and provide information about the content product defined in the "Food category" item in Table 1 (e.g. prepared fruits);
- **Extent of the function or service:** defined capacity/weight of the packaged product defined in the "Capacity" item in in Table 1 (e.g. 400 ml);

<sup>1</sup> Zampori, L. and Pant, R., Suggestions for updating the Product Environmental Footprint (PEF) method, EUR 29682 EN, Publications Office of the European Union, Luxembourg, 2019, ISBN 978-92-76- 00654-1, doi:10.2760/424613, JRC11595. <https://publications.jrc.ec.europa.eu/repository/handle/JRC115959>

<sup>2</sup> Zampori, L. and Pant, R., Suggestions for updating the Product Environmental Footprint (PEF) method, EUR 29682 EN, Publications Office of the European Union, Luxembourg, 2019, ISBN 978-92-76- 00654-1, doi:10.2760/424613, JRC11595. §3.2.1 Functional unit and reference flow



- **Expected level of quality:** guarantee food safety performances and shelf-life;
- **Duration/life time of the product :** equal to the expected shelf-life;
- **Reference flow:** the amount of product needed to fulfill the defined function that shall be measured in grams of packaging material(s).

## 4.2. System boundary

The nine food categories selected for reuse in R3PACK project have been: prepared fruits, prepared salad, yoghurt, cheese, chips, in-shop products, savory biscuits, milk and juice. The project partners have selected a representative product for each category and are those in Table 1. Two products have been selected for the yoghurt category, one for Greek yoghurt and another for sour cream, two products have been selected for the milk category, one made by PET and one made by PEHD; two products have been selected for the Savory biscuits category. The analyses will consider **primary packaging** raw material acquisition and pre-processing, manufacturing, distribution stage, use stage and end-of-life. Secondary packaging, packaging-related food waste, packaging geometric features (e.g. emptyability) and the packaging filling phase will be excluded from the system boundary for this state of the art analysis, but they would be re-discussed for the possible integration in face of the comparative analysis of the developed solutions for reuse in D6.3 Part B. All the processes attributed to the packaging are listed in the Life Cycle Inventory (LCI) divided by life cycle stages. Here below, a list of the processes considered for each stage is provided:

- **Raw material acquisition and pre-processing:** this life cycle stage begins when resources are extracted from nature and ends when product components enter the packaging production plant. In particular, it includes the pre-processing of material inputs. The transportation related to the acquisition of raw material is partly modelled by SimaPro (embedded in the Market processes, selected whenever available).
- **Manufacturing:** the production stage begins when the product components enter the production site and ends when the finished product leaves the production facility. The transportation related to the acquisition of material is partly modelled by SimaPro (embedded in the Market processes, selected whenever available).
- **Distribution stage/Use stage:** this phase corresponds to the packaged product's distribution and storage (warehouse/retail). For substitution, it won't be associated with any process both for the lack of primary data and considering that with the same functional unit (that should be adopted to establish comparative analyses in the following deliverables), impacts related to distribution and use stage are comparable between the state-of-the-art packaging and the one manufactured with newly developed materials. In the occurrence of substantial differences related to these phases between the state-of-the-art and new solutions, it will be necessary to retrieve and implement primary data relating to the two scenarios to structure a comparison.
- **End-of-life:** this stage begins when the user disposes of the packaging and ends when it is returned to nature as a waste product or enters another product's life cycle (i.e. as a recycled input). In this case, recycling operations, incineration and landfilling are considered. The following analyses will account for incineration and landfilling-related contributions to define the impact assessment results. At the same time, processes that offer environmental benefits, such as recycling and energy recovery, are excluded from the calculation due to the cut-off approach that will be described later. A specific waste scenario has been modelled for the





analyses considering French data on packaging EoL.

- **System boundary diagram:** the following map in Figure 1 shows the different life cycle stages considered. Pre-processing and Manufacturing phases are merged in the process inventory and in the presentation of the results. As described above, distribution and use are not associated with any flow.




Figure 1: System boundaries diagram.

### 4.3. Environmental Footprint impact categories

LCA results are presented through various environmental impact categories. For the impact assessment all the 16 EF (Environmental Footprint) impact categories shown in Table 2 are considered together with an all-encompassing value expressed in Pt obtained by weighting the different categories through appropriate factors. In the interpretation phase, only the most relevant impact categories are considered. Table 2 shows the list of all the EF impact categories and related indicators and units are provided<sup>3</sup>.

Tab 2. EF impact categories and related indicators and units.

EF Impact category	Impact category Indicator	Unit	Characterization model
<b>Climate change, total<sup>4</sup></b>	Radiative forcing as global warming potential (GWP100)	kg CO2 eq	Baseline model of 100 years of the IPCC (based on IPCC 2013)
<b>Ozone depletion</b>	Ozone Depletion Potential (ODP)	kg CFC-11 eq	Steady-state ODPs as in (WMO 2014 + integrations)
<b>Human toxicity, cancer</b>	Comparative Toxic Unit for humans (CTUh)	CTUh	USEtox model 2.1 (Fankte et al, 2017)
<b>Human toxicity, non-cancer</b>	Comparative Toxic Unit for humans (CTUh)	CTUh	USEtox model 2.1 (Fankte et al, 2017)

<sup>3</sup> Zampori, L. and Pant, R., Suggestions for updating the Product Environmental Footprint (PEF) method, EUR 29682 EN, Publications Office of the European Union, Luxembourg, 2019, ISBN 978-92-76- 00654-1, doi:10.2760/424613, JRC11595. § 3.2.3 Environmental Footprint impact categories, Tab. 2

<sup>4</sup> The indicator "Climate Change, total" is constituted by three sub-indicators: Climate Change, fossil; Climate Change, biogenic; Climate Change, land use and land use change. The sub-indicators are further described in section 4.4.10. The sub-categories 'Climate change –fossil', 'Climate change – biogenic' and 'Climate change - land use and land use change', shall be reported separately if they show a contribution of more than 5% each to the total score of climate change.



Funded by the European Union

This project has received funding from the European Union's Horizon Europe Research and Innovation programme under Grant Agreement No 101060806. This document reflects the views of the author(s) and does not necessarily reflect the views or policy of the European Commission. Whilst efforts have been made to ensure the accuracy and completeness of this document, the European Commission shall not be liable for any errors or omissions, however

<b>Particulate matter</b>	Impact on human health	disease incidence	PM method recomended by UNEP (UNEP 2016)
<b>Ionising radiation, human health</b>	Human exposure efficiency relative to U235	kBq U235 eq	Human health effect model as developed by Dreicer et al. 1995 (Frischknecht et al, 2000)
<b>Photochemical ozone formation, human health</b>	Tropospheric ozone concentration increase	kg NMVOC eq	LOTOS-EUROS model (Van Zelm et al, 2008) as implemented in ReCiPe 2008
<b>Acidification</b>	Accumulated Exceedance (AE)	mol H+ eq	Accumulated Exceedance (Seppälä et al. 2006, Posch et al, 2008)
<b>Eutrophication, terrestrial</b>	Accumulated Exceedance (AE)	mol N eq	Accumulated Exceedance (Seppälä et al. 2006, Posch et al, 2008)
<b>Eutrophication, freshwater</b>	Fraction of nutrients reaching freshwater end compartment (P)	kg P eq	EUTREND model (Struijs et al, 2009) as implemented in ReCiPe
<b>Eutrophication, marine</b>	Fraction of nutrients reaching marine end compartment (N)	kg N eq	EUTREND model (Struijs et al, 2009) as implemented in ReCiPe
<b>Ecotoxicity, freshwater</b>	Comparative Toxic Unit for ecosystems (CTUe)	CTUe	USEtox model 2.1 (Fankte et al, 2017)
<b>Land use</b>	<ul style="list-style-type: none"> <li>• Soil quality index<sup>5</sup></li> <li>• Biotic production</li> <li>• Erosion resistance</li> <li>• Mechanical filtration</li> <li>• Groundwater replenishment</li> </ul>	<ul style="list-style-type: none"> <li>• Dimensionless (pt)</li> <li>• kg biotic production</li> <li>• kg soil</li> <li>• m3 water</li> <li>• m3 groundwater</li> </ul>	Soil quality index based on LANCA (Beck et al. 2010 and Bos et al. 2016)
<b>Water use</b>	User deprivation potential (deprivation-weighted water consumption)	m3 world eq	Available WATER Remaining (AWARE) as recommended by UNEP, 2016
<b>Resource use<sup>6</sup>, minerals and metals</b>	Abiotic resource depletion (ADP ultimate reserves)	kg Sb eq	CML 2002 (Guinée et al., 2002) and van Oers et al. 2002.
<b>Resource use, fossils</b>	Abiotic resource depletion – fossil fuels (ADP-fossil) <sup>7</sup>	MJ	CML 2002 (Guinée et al., 2002) and van Oers et al. 2002

## 5. LIFE CYCLE INVENTORY ANALYSIS

### 5.1. Data collection and quality

#### DATA COLLECTION

To build the life cycle inventory (LCI), a data collection form was sent to the partners involved. Given the scarcity of data recovered from the data collection T1, a simplified version of the form was formulated to retrieve the essential primary data necessary to conduct the analyses.

Tab. 3 shows a *fac-simile* of the data collection model: the partners were asked to specify, for each layer of the packaging, the material (possibly accompanied by the relative technical datasheet), the weight in grams of the layer itself and its manufacturing process(es). Partners were also asked to indicate packaging nominal capacity, the overall production technology and to provide a reference image of the product.

Tab 3. Fac-simile of data collection model


<sup>5</sup> This index is the result of the aggregation, performed by JRC, of the 4 indicators provided by LANCA model as indicators for land use.

<sup>6</sup> The results of this impact category shall be interpreted with caution, because the results of ADP after normalization may be overestimated. The European Commission intends to develop a new method moving from depletion to dissipation model to better quantify the potential for conservation of resources

<sup>7</sup> In the EF flow list, and for the current recommendation, Uranium is included in the list of energy carriers, and it is measured in MJ.



<b>Name of the product</b>		BEVERAGE MULTILAYER	
<b>Packaging capacity</b>		1 L	
<b>PRODUCT COMPOSITION - INBOUND OF RAW MATERIALS</b>			
	<b>Commercial name of the product (Material Data Sheet)</b>	<b>Weight (g)</b>	<b>Process technology</b>
<b>PACKAGING BODY</b>			
<i>First layer</i>	<i>Solid bleached and unbleached board carton</i>	11	<i>(Sulfate pulp production)</i>
<i>Aluminum foil</i>	<i>aluminum</i>	2.7	
<i>Adhesive</i>	<i>Vinyl acetate</i>	0.2	
<i>Ink</i>	<i>printing ink</i>	0.05	
<i>Varnish</i>	<i>mix of organic and inorganic compound</i>	0.05	
<b>Packaging production technology</b>	LAMINATION		



## DATA QUALITY

With regard to materials, in most cases was indicated the general type of material (e.g. PET, aluminium, etc.), but not the exact grade and composition; for this reason, data retrieved from the databases available in SimaPro were used, specifically the Ecoinvent database<sup>8</sup>, considering material grades suitable for food packaging. Similarly, for processes (e.g. extrusion, rolling, etc.) Ecoinvent databases were considered as well.

The retrieved data from partners are reported in Annex 1 at the end of this document.

## 5.2. LCI organization

In this paragraph, the inventory tables are provided and organized to keep the various phases of the packaging life cycle separate as described in the system boundary diagram.

### PRE-PROCESSING AND MANUFACTURING LCI

Here below, for each product, a table describing the pre-processing (PP) and manufacturing (M) processes of the packaging is provided. The inventory is structured as a bill of materials: each component that makes the product up is associated with a position number that reflects the structure of the assemblies; quantity and weight in grams are indicated for each component/assembly.

Regarding pre-processing, the material (as declared by the company in the data collection form) is indicated for each layer, together with the corresponding raw material selected in SimaPro. With respect to manufacturing, a description of the processes used and an indication of the corresponding processes in SimaPro is provided. If the original datasets have been modified to adapt them to the French context by selecting, for example, energy data related to this geographical area, all the modifications made are reported in a dedicated column.

In correspondence with each table, any limitations and assumptions made during the compilation of the inventory are reported.

<sup>8</sup> Further information on Ecoinvent databases are available at <https://ecoinvent.org>



• **TABLE A1, PP-M LCI, PRODUCT 01 – Florette Shaker, PET Cup**

Assumptions and limitations: the heat sealing process for components 1.1 and 1.2 has been omitted due to the lack of specific information retrieved in the data collection and suitable Ecoinvent datasets. Furthermore, no information has been provided regarding eventual printing processes and related ink, which therefore were not included in the analysis.

Tab A1. PP-M LCI, PRODUCT 01 – Florette Shaker, PET Cup

Table A1				Pre-processing		Manufacturing		
Position	Description	Quantity	Weight (g)	Material	Material (SimaPro)	Processing	Processing (Original SimaPro dataset)	Processing variations (available FR datasets)
1	PET Cup	1	12,4	/	/	Heat sealing	/	/
1.1	PET Foil Lid	1	0,8	PET	Polyethylene terephthalate, granulate, amorphous {RER}  production   Cut-off, U	Extrusion of plastic film	Extrusion, plastic film {RER}  extrusion, plastic film   Cut-off, U	<ul style="list-style-type: none"> <li>• Water, cooling, unspecified natural origin, FR;</li> <li>• Electricity, medium voltage {FR}  market for   Cut-off, U</li> </ul>
1.2	PET Shaker	1	11,6	PET	Polyethylene terephthalate, granulate, amorphous {RER}  production   Cut-off, U	Extrusion of plastic sheets and thermoforming	Extrusion of plastic sheets and thermoforming, inline {FR}  processing   Cut-off, U	/

• **TABLE A2, PP-M LCI, PRODUCT 02 – Salad MDD, PET Tray**

Assumptions and limitations: no information has been provided regarding eventual printing processes and related inks or other labels, which therefore were not included in the analysis.

Tab A2. PP-M LCI, PRODUCT 02 – Salad MDD, PET Tray

Table A2				Pre-processing		Manufacturing		
Position	Description	Quantity	Weight (g)	Material	Material (SimaPro)	Processing	Processing (Original SimaPro dataset)	Processing variations (available FR datasets)
2	PET Tray	1	30	/	/	Inline manual closing	/	/
2.1	PET Lid	1	10	PET	Polyethylene terephthalate, granulate, amorphous {RER}  production   Cut-off, U	Extrusion of plastic sheets and thermoforming	Extrusion of plastic sheets and thermoforming, inline {FR}  processing   Cut-off, U	/
2.2	PET Bowl	1	20	PET	Polyethylene terephthalate, granulate, amorphous {RER}  production   Cut-off, U	Extrusion of plastic sheets and thermoforming	Extrusion of plastic sheets and thermoforming, inline {FR}  processing   Cut-off, U	/



- TABLE A3, PP-M LCI, PRODUCT 03 – Sour cream, Cup**

Assumptions and limitations: the sealing process for components 3.2 and 3.3 and the closing process for components 3.1 and 3.3 have been omitted due to the lack of specific information retrieved in the data collection and suitable Ecoinvent datasets. The manufacturing process for the monolayer Aluminium Lid (3.2) was not declared, thus, sheet rolling was assumed as the most suitable option. Furthermore, no information has been provided regarding eventual printing processes and related ink, which therefore were not included in the analysis.

*Tab A3. PP-M LCI, PRODUCT 03 – Sour cream, Cup*

Table A3				Pre-processing		Manufacturing		
Position	Description	Quantity	Weight (g)	Material	Material (SimaPro)	Processing	Processing (Original SimaPro dataset)	Processing variations (available FR datasets)
3	Cup	1	12,36	/	/	Inline closing and sealing	/	/
3.1	PET Overcap	1	3,05	PET	Polyethylene terephthalate, granulate, amorphous {RER}   production   Cut-off, U	Extrusion of plastic sheets and thermoforming	Extrusion of plastic sheets and thermoforming, inline {FR}   processing   Cut-off, U	/
3.2	Aluminium Lid	1	0,81	Aluminium	Aluminium alloy, AlMg3 {GLO}   market for   Cut-off, U	Sheet rolling	Sheet rolling, aluminium {RER}   processing   Cut-off, U	<ul style="list-style-type: none"> <li>• Water, unspecified natural origin, FR;</li> <li>• Electricity, medium voltage {FR}   market for   Cut-off, U</li> </ul>
3.3	PP Bowl	1	8,5	PP	Polypropylene, granulate {RER}   production   Cut-off, U	Extrusion of plastic sheets and thermoforming	Extrusion of plastic sheets and thermoforming, inline {FR}   processing   Cut-off, U	/



• **TABLE A4, PP-M LCI, PRODUCT 04 – Greek yoghurt, Cup**

Assumptions and limitations: the sealing process for components 4.2 and 4.3 and the closing process for components 4.1 and 4.3 have been omitted due to the lack of specific information retrieved in the data collection and suitable Ecoinvent datasets. The manufacturing process for the monolayer Aluminium Lid (4.2) was not declared, thus, sheet rolling was assumed as the most suitable option. Furthermore, no information has been provided regarding eventual printing processes and related ink, which therefore were not included in the analysis.

Tab A4. PP-M LCI, PRODUCT 04 – Greek yoghurt, Cup

Table A4				Pre-processing		Manufacturing		
Position	Description	Quantity	Weight (g)	Material	Material (SimaPro)	Processing	Processing (Original SimaPro dataset)	Processing variations (available FR datasets)
4	Cup	1	20,25	/	/	Inline closing and sealing	/	/
4.1	PET Overcap	1	5	PET	Polyethylene terephthalate, granulate, amorphous {RER}   production   Cut-off, U	Extrusion of plastic sheets and thermoforming	Extrusion of plastic sheets and thermoforming, inline {FR}   processing   Cut-off, U	/
4.2	Aluminium Lid	1	1,25	Aluminium	Aluminium alloy, AlMg3 {GLO}   market for   Cut-off, U	Sheet rolling	Sheet rolling, aluminium {RER}   processing   Cut-off, U	<ul style="list-style-type: none"> <li>• Water, unspecified natural origin, FR;</li> <li>• Electricity, medium voltage {FR}   market for   Cut-off, U</li> </ul>
4.3	PP Bowl	1	14	PP	Polypropylene, granulate {RER}   production   Cut-off, U	Extrusion of plastic sheets and thermoforming	Extrusion of plastic sheets and thermoforming, inline {FR}   processing   Cut-off, U	/



• **TABLE A5, PP-M LCI, PRODUCT 05 – Pork chop, Wrapped Tray**

Note: for the “In-shop products” food category a specific EPS tray was not supplied by the partners, therefore a suitable one for the reference product (2 pork chops) was selected by the authors. Specifically, the product is made up of an expanded polystyrene tray and a PVC film.

Assumptions and limitations: the wrapping process (manual or automatic) has been omitted as considered negligible and due to the absence of suitable Ecoinvent datasets.

Tab A5. PP-M LCI, PRODUCT 05 – Pork chop, Wrapped Tray

Table A5				Pre-processing		Manufacturing		
Position	Description	Quantity	Weight (t)	Material	Material (SimaPro)	Processing	Processing (Original SimaPro dataset)	Processing variations (available FR datasets)
5	Wrapped Tray	1	13,8	/	/	Wrapping	/	/
5.1	PVC Wrapping Film	1	2,9	PVC	Polyvinylchloride, suspension polymerised {RER}   polyvinylchloride production, suspension polymerisation   Cut-off, U	Bubble extrusion of plastic film	Extrusion, plastic film {RER}   extrusion, plastic film   Cut-off, U	<ul style="list-style-type: none"> <li>• Water, cooling, unspecified natural origin, FR;</li> <li>• Electricity, medium voltage {FR}   market for   Cut-off, U</li> </ul>
5.2	PSE Tray	1	10,9	EPS	Polystyrene, expandable {RER}   production   Cut-off, U	Extrusion of plastic sheets and thermoforming	Extrusion of plastic sheets and thermoforming, inline {FR}   processing   Cut-off, U	/
						Foaming	Polymer foaming {RER}   processing   Cut-off, U	<ul style="list-style-type: none"> <li>• Water, cooling, unspecified natural origin, FR;</li> <li>• Electricity, medium voltage {FR}   market for   Cut-off, U</li> </ul>



• **TABLE A8, PP-M LCI, PRODUCT 08 – Grated cheese, OPA & LDPE Film**

Assumptions and limitations: The printing process has been omitted due to the absence of suitable Ecoinvent datasets, only the date of ink has been considered.

Tab A8. PP-M LCI, PRODUCT 08 – Grated cheese, OPA & LDPE Film

Table A8				Pre-processing		Manufacturing		
Position	Description	Quantity	Weight (g)	Material	Material (SimaPro)	Processing	Processing (Original SimaPro dataset)	Processing variations (available FR datasets)
8	Grated Cheese Bag	1	5,06	/	/	/		/
8.1	OPA & LDPE Film	1	0,11	Ink	Printing ink, offset, without solvent, in 47% solution state {RER}	Printing Ink	/	/
8.2	Complexing Film	1	0,15	Adhesive	Acrylic binder, with water, in 54% solution state {RER}   Cut-off, U	Lamination	Laminating service, foil, with acrylic binder {RER}  processing   Cut-off, U	• Electricity, medium voltage {FR}  market for   Cut-off, U
8.3	LDPE Foil	1	3,5	LDPE	Polyethylene terephthalate, granulate, amorphous {RER}  production   Cut-off, U	Extrusion of plastic film	Extrusion, plastic film {RER}  extrusion, plastic film   Cut-off, U	• Water, cooling, unspecified natural origin, FR; • Electricity, medium voltage {FR}  market for   Cut-off, U
8.4	OPA Foil	1	1,3	PA	Nylon 6 {RER}  production   Cut-off, U	Extrusion of plastic film	Extrusion, plastic film {RER}  extrusion, plastic film   Cut-off, U	• Water, cooling, unspecified natural origin, FR; • Electricity, medium voltage {FR}  market for   Cut-off, U





• **TABLE A9, PP-M LCI, PRODUCT 09 – Peanut curl, OPP Film**

Assumptions and limitations: The Metallization process for OPP film (9.2) has been omitted due to the lack of specific information retrieved in the data collection (type of metal and type of process). The printing process has been omitted due to the absence of suitable Ecoinvent datasets, only the date of ink has been considered.

Tab A9. PP-M LCI, PRODUCT 09 – Peanut curl, OPP Film

Table A9				Pre-processing		Manufacturing		
Position	Description	Quantity	Weight (g)	Material	Material (SimaPro)	Processing	Processing (Original SimaPro dataset)	Processing variations (available FR datasets)
9	Bag	1	5,57	/	/	/		/
9.1	OPP Film	1	0,414	Ink	Printing ink, offset, without solvent, in 47% solution state {RER}	Printing Ink	/	/
9.2	OPP Film	1	0,296	Adhesive	Acrylic binder, with water, in 54% solution state {RER}   Cut-off, U	Lamination	Laminating service, foil, with acrylic binder {RER}  processing   Cut-off, U	• Electricity, medium voltage {FR}  market for   Cut-off, U
9.3	PP Foil	1	4,86	PP	Polypropylene, granulate {RER}  production   Cut-off, U	Extrusion of plastic film	Extrusion, plastic film {RER}  extrusion, plastic film   Cut-off, U	• Water, cooling, unspecified natural origin, FR; • Electricity, medium voltage {FR}  market for   Cut-off, U

• **TABLE A10, PP-M LCI, PRODUCT 10 – Savory biscuits, OPP & Cardboard**

Assumptions and limitations: The metallization process for OPP film (10.2) has been omitted due to the lack of specific information retrieved in the data collection (type of metal and type of process).

For the Cardboard box (10.1) has been used a dataset for production of a Folding boxboard carton that haven't specific data on recycled cardboard.



Tab A10. PP-M LCI, PRODUCT 10 – Savory biscuits, OPP &amp; Cardboard

Table A10				Pre-processing		Manufacturing		
Position	Description	Quantity	Weight (g)	Material	Material (Simapro)	Processing	Processing (Original Simapro dataset)	Processing variations (available FR datasets)
10	Savory Biscuit	1	25,75	/	/	/		
10.1	Cardboard Box	1	24			Flat cut	Folding boxboard carton production {RER}   production   Cut-off, U	<ul style="list-style-type: none"> <li>Variation amount of Varnish and Ink</li> <li>Electricity, medium voltage {FR}   market for   Cut-off, U</li> </ul>
10.2	OPP Film	1	0,15	Adhesive	Acrylic binder, with water, in 54% solution state {RER}   Cut-off, U	Lamination	Laminating service, foil, with acrylic binder {RER}   processing   Cut-off, U	<ul style="list-style-type: none"> <li>Electricity, medium voltage {FR}   market for   Cut-off, U</li> </ul>
10.3	PP Foil	1	1,6	PP	Polypropylene, granulate {RER}   production   Cut-off, U	Extrusion of plastic film	Extrusion, plastic film {RER}   extrusion, plastic film   Cut-off, U	<ul style="list-style-type: none"> <li>Water, cooling, unspecified natural origin, FR;</li> <li>Electricity, medium voltage {FR}   market for   Cut-off, U</li> </ul>

• **TABLE A11, PP-M LCI, PRODUCT 11 – Orange Juice- PET Clear Bottle**

Assumptions and limitations: Printing processes and inks on OPP label: omitted due to the lack of specific information retrieved in the data collection.

Tab A11. PP-M LCI, PRODUCT 11 – Orange Juice- PET Clear Bottle

Position	Description	Quantity	Weight (g)	Material	Material (Simapro)	Processing	Processing (Original Simapro dataset)	Processing variations (available FR datasets)
11	Clear bottle	1	32	/	/	Capping	/	/
11.1	HDPE Cap	1	3	HDPE	Polyethylene, high density, granulate {RER}   polyethylene production, high density, granulate   Cut-off, U	Injection moulding	Injection moulding {RER}   injection moulding   Cut-off, U	<ul style="list-style-type: none"> <li>Water, cooling, unspecified natural origin, FR;</li> <li>Electricity, medium voltage {FR}   market for   Cut-off, U</li> </ul>
11.2	OPP Foil	1	1	PP	Polypropylene, granulate {RER}   production   Cut-off, U	Extrusion of plastic film	Extrusion, plastic film {RER}   extrusion, plastic film   Cut-off, U	<ul style="list-style-type: none"> <li>Water, cooling, unspecified natural origin, FR;</li> <li>Electricity, medium voltage {FR}   market for   Cut-off, U</li> </ul>
11.3	PET Bottle	1	14	PET	Polyethylene terephthalate, granulate, bottle grade {RER}   polyethylene terephthalate production, granulate, bottle grade   Cut-off, U	Stretch blow moulding	Stretch blow moulding {RER}   stretch blow moulding   Cut-off, U	<ul style="list-style-type: none"> <li>Water, cooling, unspecified natural origin, FR;</li> <li>Electricity, medium voltage {FR}   market for   Cut-off, U</li> </ul>
			14	rPET	Polyethyleneterephthalate, granulate, bottle grade, recycled {CH}   polyethylene terephthalate production, granulate, bottle grade, recycled   Cut-off, U	Injection moulding	Injection moulding {RER}   injection moulding   Cut-off, U	<ul style="list-style-type: none"> <li>Water, cooling, unspecified natural origin, FR;</li> <li>Electricity, medium voltage {FR}   market for   Cut-off, U</li> </ul>



• **TABLE A12, PP-M LCI, PRODUCT 12 – UHT Milk – PET Opaque Bottle**

Assumptions and limitations: Printing processes and inks on OPP label has been omitted due to the lack of specific information retrieved in the data collection.

Tab A12. PP-M LCI, PRODUCT 12 – UHT Milk – PET Opaque Bottle

Table A12				Pre-processing		Manufacturing		
Position	Description	Quantity	Weight (g)	Material	Material (Simapro)	Processing	Processing (Original Simapro datasets)	Processing variations (available FR datasets)
12	Opaque bottle	1	28	/	/	Capping	/	/
12.1	HDPE Cap	1	3	HDPE	Polyethylene, high density, granulate {RER}   polyethylene production, high density, granulate   Cut-off, U	Injection moulding	Injection moulding {RER}   injection moulding   Cut-off, U	<ul style="list-style-type: none"> <li>• Water, cooling, unspecified natural origin, FR;</li> <li>• Electricity, medium voltage {FR}   market for   Cut-off, U</li> </ul>
12.2	OPP Foil	1	1	PP	Polypropylene, granulate {RER}   production   Cut-off, U	Extrusion of plastic film	Extrusion, plastic film {RER}   extrusion, plastic film   Cut-off, U	<ul style="list-style-type: none"> <li>• Water, cooling, unspecified natural origin, FR;</li> <li>• Electricity, medium voltage {FR}   market for   Cut-off, U</li> </ul>
12.3	PET Bottle	1	12	PET	Polyethylene terephthalate, granulate, bottle grade {RER}   polyethylene terephthalate production, granulate, bottle grade   Cut-off, U	Stretch blow moulding	Stretch blow moulding {RER}   stretch blow moulding   Cut-off, U	<ul style="list-style-type: none"> <li>• Water, cooling, unspecified natural origin, FR;</li> <li>• Electricity, medium voltage {FR}   market for   Cut-off, U</li> </ul>
			12	rPET	Polyethylene terephthalate, granulate, bottle grade, recycled {CH}   polyethylene terephthalate production, granulate, bottle grade, recycled   Cut-off, U	Injection moulding	Injection moulding {RER}   injection moulding   Cut-off, U	<ul style="list-style-type: none"> <li>• Water, cooling, unspecified natural origin, FR;</li> <li>• Electricity, medium voltage {FR}   market for   Cut-off, U</li> </ul>

• **TABLE A13, PP-M LCI, PRODUCT 13 – UHT Milk – PEHD Bottle**

Assumptions and limitations: Label material, printing processes and inks has been omitted due to the lack of specific information retrieved in the data collection



Tab A13. PP-M LCI, PRODUCT 13 – UHT Milk – PEHD Bottle

Table A13				Pre-processing		Manufacturing		
Position	Description	Quantity	Weight (g)	Material	Material (SimaPro)	Processing	Processing (Original SimaPro dataset)	Processing variations (available FR datasets)
13	HDPE bottle	1	35,7	/	/	Capping		/
13.1	HDPE Cap	1	2,7	HDPE	Polyethylene, high density, granulate {RER}  polyethylene production, high density, granulate   Cut-off, U	Injection moulding	Injection moulding {RER}  injection moulding   Cut-off, U	<ul style="list-style-type: none"> <li>Water, cooling, unspecified natural origin, FR;</li> <li>Electricity, medium voltage {FR}  market for   Cut-off, U</li> </ul>
13.2	Bottle	1	33	HDPE	Polyethylene, high density, granulate {RER}  polyethylene production, high density, granulate   Cut-off, U	Stretch blow moulding	Stretch blow moulding {RER}  stretch blow moulding   Cut-off, U	<ul style="list-style-type: none"> <li>Water, cooling, unspecified natural origin, FR;</li> <li>Electricity, medium voltage {FR}  market for   Cut-off, U</li> </ul>
						Co-extrusion	Extrusion, co-extrusion {FR}  extrusion, co-extrusion of plastic sheets   Cut-off, U	/

• **TABLE A14, PP-M LCI, PRODUCT - 14 Savory biscuits, BOPP & Cardboard**

Assumptions and limitations: Dataset for production of a Folding boxboard carton haven't specific data on recycled cardboard.

The Coating process has been omitted due to the lack of specific information retrieved in the data collection.

The Printing process has been omitted due to the absence of suitable Ecoinvent datasets.

Tab A14. PP-M LCI, PRODUCT 14 – Savory biscuits, BOPP &amp; Cardboard

Table A14				Pre-processing		Manufacturing		
Position	Description	Quantity	Weight (g)	Material	Material (SimaPro)	Processing	Processing (Original SimaPro dataset)	Processing variations (available FR datasets)
14	Savory Biscuit	1	30	/	/	/		/
14.1	Cardboard Box	1	27		/	Flat cut	Folding boxboard carton production {RER}  production   Cut-off, U	<ul style="list-style-type: none"> <li>Variation amount of Varnish and Ink</li> <li>Electricity, medium voltage {FR}  market for   Cut-off, U</li> </ul>
14.2	BOPP Foil	1	3	PP	Polypropylene, granulate {RER}  production   Cut-off, U	Extrusion of plastic film	Extrusion, plastic film {RER}  extrusion, plastic film   Cut-off, U	<ul style="list-style-type: none"> <li>Water, cooling, unspecified natural origin, FR;</li> <li>Electricity, medium voltage {FR}  market for   Cut-off, U</li> </ul>



**END-OF-LIFE LCI**

Regarding the LCI of the end-of-life phase, a dedicated waste scenario has been defined for each material. Each waste scenario is composed of the different waste treatments i.e. recycling, incineration and landfill. The percentage of wasted material destined for each waste treatment was defined on the basis of data relating to waste management in the French context; the sources are indicated in the “data source” column (Tab. B). Furthermore, the table below shows the process with which each waste treatment is modelled in SimaPro. The specific waste scenario for each product consists of a single waste process if the product is mono-material, or of the combination of two or more waste processes if the product is made up of components in different materials; in the latter case, the percentages of material destined for each waste process are defined on the basis of weight percentage of each material on the packaging composition.



• **TABLE B, EOL LCI**

Tab B. END-OF-LIFE LCI

		Table B				End of Life		
	Waste type	Material % per waste treatment	Data description	Data source	Waste treatment	Waste treatment (Simapro dataset)	Notes	
Waste scenario	Waste process	PA	27	France post-consumer plastics packaging waste treatment	Plastics Europe, 2022	PA Recycling	PA (waste treatment) {GLO}   recycling of PA   Cut-off, U	
			44	France post-consumer plastics packaging waste treatment	Plastics Europe, 2022	PA Incineration	Waste plastic, mixture {CH}   treatment of waste plastic, mixture, municipal incineration   Cut-off, U	
			29	France post-consumer plastics packaging waste treatment	Plastics Europe, 2022	PA Landfill	Waste plastic, mixture {CH}   treatment of waste plastic, mixture, sanitary landfill   Cut-off, U	
	Waste process	PET	27	France post-consumer plastics packaging waste treatment	Plastics Europe, 2022	PET Recycling	PET (waste treatment) {GLO}   recycling of PET   Cut-off, U	
			44	France post-consumer plastics packaging waste treatment	Plastics Europe, 2022	PET Incineration	Waste polyethylene terephthalate {CH}   treatment of waste polyethylene terephthalate, municipal incineration   Cut-off, U	
			29	France post-consumer plastics packaging waste treatment	Plastics Europe, 2022	PET Landfill	Waste polyethylene terephthalate {CH}   treatment of waste polyethylene terephthalate, sanitary landfill   Cut-off, U	
	Waste process	PP	27	France post-consumer plastics packaging waste treatment	Plastics Europe, 2022	PP Recycling	PP (waste treatment) {GLO}   recycling of PP   Cut-off, U	
			44	France post-consumer plastics packaging waste treatment	Plastics Europe, 2022	PP Incineration	Waste polypropylene {CH}   treatment of, municipal incineration   Cut-off, U	
			29	France post-consumer plastics packaging waste treatment	Plastics Europe, 2022	PP Landfill	Waste polypropylene {CH}   treatment of, sanitary landfill   Cut-off, U	
	Waste process	PVC	27	France post-consumer plastics packaging waste treatment	Plastics Europe, 2022	PVC Recycling	PVC (waste treatment) {GLO}   recycling of PVC   Cut-off, U	
			44	France post-consumer plastics packaging waste treatment	Plastics Europe, 2022	PVC Incineration	Waste polyvinylchloride {CH}   treatment of, municipal incineration   Cut-off, U	
			29	France post-consumer plastics packaging waste treatment	Plastics Europe, 2022	PVC Landfill	Waste polyvinylchloride {CH}   treatment of, sanitary landfill   Cut-off, U	
	Waste process	EPS	27	France post-consumer plastics packaging waste treatment	Plastics Europe, 2022	EPS Recycling	PS (waste treatment) {GLO}   recycling of PS   Cut-off, U	
			44	France post-consumer plastics packaging waste treatment	Plastics Europe, 2022	EPS Incineration	Waste expanded polystyrene {CH}   treatment of, municipal incineration   Cut-off, U	
			29	France post-consumer plastics packaging waste treatment	Plastics Europe, 2022	EPS Landfill	Waste polystyrene {CH}   treatment of, sanitary landfill   Cut-off, U	datasets for PS
	Waste process	Aluminium	58	France post-consumer aluminium packaging waste treatment	Citeo Adelphe, 2021	Aluminium Recycling	Aluminium (waste treatment) {GLO}   recycling of aluminium   Cut-off, U	
			42	France MSW treatment	Eurostat, 2018	Municipal Waste (62% Incineration + 38% Landfill)	Municipal solid waste {FR}   market for municipal solid waste   Cut-off, U	
	Waste process	Aluminium&OPP	100	France MSW treatment	Eurostat, 2018	Municipal Waste	Municipal solid waste {FR}   Cut-off, U	
	Waste process	Cardboard	72	France post-consumer cardboard packaging waste treatment	Citeo Adelphe, 2021	Paper Recycling	Paper (waste treatment) {GLO}   recycling of paper   Cut-off, U	
			28	France MSW treatment	Eurostat, 2018	Municipal Waste	Waste paperboard {FR}   market for waste paperbord   Cut-off, U	



Funded by the European Union

This project has received funding from the European Union's Horizon Europe Research and Innovation programme under Grant Agreement No 101060806. This document reflects the views of the author(s) and does not necessarily reflect the views or policy of the European Commission. Whilst efforts have been made to ensure the accuracy and completeness of this document, the European Commission shall not be liable for any errors or omissions, however

## END-OF-LIFE MODELLING CHOICES

To date, a cut-off approach has been applied to the end-of-life modeling which excludes from the calculation of the impact those processes that bring environmental benefits. This means that credits and impacts connected to recycling and secondary energy derived from energy recovery processes are equal to zero (Fig.2). The impacts that are calculated in the end-of-life scenario therefore concern incineration and disposal in landfill.




Figure 2: An example of waste process

In order to calculate credits and impacts connected to recycling and energy recovery in the PEF Method, the use of the Circular Footprint Formula (CFF) is prescribed<sup>9</sup>. CFF is composed of three parts corresponding, respectively, to material, energy and disposal (Fig. 3).




Figure 3: Circular Footprint Formula (CFF)

<sup>9</sup> Zampori, L. and Pant, R., Suggestions for updating the Product Environmental Footprint (PEF) method, EUR 29682 EN, Publications Office of the European Union, Luxembourg, 2019, ISBN 978-92-76- 00654-1, doi:10.2760/424613, JRC11595. § 4.4.8.1 The Circular Footprint Formula (CFF)



The CFF allows the connection with subsequent and preceding life cycles via debiting (Fig. 4, left) and crediting (Fig. 4, right) which in the cut-off approach, are not considered<sup>10</sup>.




Figure 4: CFF debiting (left) and crediting (right)

Circular Footprint Formula is likely to be implemented in the following deliverable thanks to the recent release of the new EF 3.1 database<sup>11</sup> containing the needed datasets for the calculation in Sima Pro.

## 6. IMPACT ASSESSMENT RESULTS

### PEF results

In this section, the impact assessment results are presented through 16 environmental impact indicators defined by the PEF method and described above at §4.3. The selected calculation method in SimaPro for the impact assessment is the EF 3.0, as defined in the Product Environmental Footprint.

For each product, results are presented as follow:

- **Characterised** results of all EF impact categories: the multiple impact contributions are transformed into results for each of the 16 impact categories through characterization factors. Each category has a specific unit of measure.
- **Normalised** and **weighted** results: by weighting the different EF impact categories through appropriate factors the relative shares of the impacts of the analysed system can be expressed in Pt. In this way it is possible to establish comparisons among different contributions.
- **Weighted results as single score** in  $\mu\text{Pt}$  for all the life cycle stages (Pre-processing and Manufacturing + End-of-Life): the weighted results are then aggregated into an all-encompassing indicator for each life cycle stage.

<sup>10</sup> Wolf, M. A., The Circular Footprint Formula (CFF) and its practical application training. Environmental Footprint (EF) transition phase, 2019. Webinar available in: <https://ec.europa.eu/environment/eusssd/videos/2019-10-08%2016.01%20The%20Circular%20Footprint%20Formula.mp4>

<sup>11</sup> Environmental Footprint database 3.1: <https://simapro.com/products/environmental-footprint-database/>





## PRODUCT 01 – Florette Shaker, PET Cup

### Characterised results

- **Characterised** results of all EF impact categories

Tab 4. Characterised results PRODUCT 01 - Florette Shaker, PET Cup

Impact category	Unit	Total	O1. Florette Shaker_PET Cup – PP+M	O1. Florette Shaker_PET Cup – EoL
Climate change	kg CO2 eq	5,41E-02	4,27E-02	1,14E-02
Ozone depletion	kg CFC11 eq	2,00E-07	2,00E-07	2,10E-11
Ionising radiation	kBq U-235 eq	1,21E-02	1,21E-02	9,26E-06
Photochemical ozone formation	kg NMVOC eq	1,29E-04	1,25E-04	3,80E-06
Particulate matter	disease inc.	1,73E-09	1,71E-09	2,16E-11
Human toxicity, non-cancer	CTUh	5,02E-10	4,77E-10	2,50E-11
Human toxicity, cancer	CTUh	2,95E-11	2,76E-11	1,87E-12
Acidification	mol H+ eq	1,79E-04	1,76E-04	2,78E-06
Eutrophication, freshwater	kg P eq	8,58E-06	8,56E-06	1,50E-08
Eutrophication, marine	kg N eq	4,34E-05	3,38E-05	9,66E-06
Eutrophication, terrestrial	mol N eq	3,49E-04	3,34E-04	1,46E-05
Ecotoxicity, freshwater	CTUe	5,66E-01	5,61E-01	4,56E-03
Land use	Pt	1,07E-01	1,05E-01	2,34E-03
Water use	m3 depriv.	1,98E-02	1,98E-02	2,64E-05
Resource use, fossils	MJ	1,14E+00	1,14E+00	1,62E-03
Resource use, minerals and metals	kg Sb eq	4,97E-07	4,97E-07	3,74E-10

### Weighted results

- Normalised and **weighted** results




Figure 5: Normalised and weighted results - PRODUCT 01 - Florette Shaker, PET Cup



Funded by  
the European Union

This project has received funding from the European Union's Horizon Europe Research and Innovation programme under Grant Agreement No 101060806. This document reflects the views of the author(s) and does not necessarily reflect the views or policy of the European Commission. Whilst efforts have been made to ensure the accuracy and completeness of this document, the European Commission shall not be liable for any errors or omissions, however

**Single score**

- Weighted results as single score in  $\mu\text{Pt}$  for all the life cycle stages (Pre-processing and manufacturing: 01. Florette Shaker\_PET Cup – PP+M; End-of-Life: 01. Florette Shaker\_PET Cup – EoL).
- For product 01 – Florette Shaker, PET Cup, the most relevant life cycle stage is PP+M (93,6%). The most relevant processes (processes details are shown in table A1) are related to component 1.2 PET Shaker and are Polyethylene terephthalate pre-processing and manufacturing.




Figure 6: Weighted results as single score in  $\mu\text{Pt}$  - PRODUCT 01 - Florette Shaker, PET Cup



**PRODUCT 02 – Salad MDD, PET Tray**

**Characterised results**

- **Characterised** results of all EF impact categories

Tab 5. Characterised results PRODUCT 02 – Salad MDD, PET Tray

Impact category	Unit	Total	02. Salad MDD_PET Tray – PP+M	02. Salad MDD_PET Tray – EoL
Climate change	kg CO2 eq	1,31E-01	1,04E-01	2,77E-02
Ozone depletion	kg CFC11 eq	4,85E-07	4,85E-07	5,08E-11
Ionising radiation	kBq U-235 eq	3,01E-02	3,00E-02	2,24E-05
Photochemical ozone formation	kg NMVOC eq	3,14E-04	3,04E-04	9,20E-06
Particulate matter	disease inc.	4,19E-09	4,14E-09	5,23E-11
Human toxicity, non-cancer	CTUh	1,22E-09	1,16E-09	6,06E-11
Human toxicity, cancer	CTUh	7,13E-11	6,68E-11	4,52E-12
Acidification	mol H+ eq	4,35E-04	4,28E-04	6,72E-06
Eutrophication, freshwater	kg P eq	2,08E-05	2,08E-05	3,64E-08
Eutrophication, marine	kg N eq	1,05E-04	8,19E-05	2,34E-05
Eutrophication, terrestrial	mol N eq	8,45E-04	8,10E-04	3,54E-05
Ecotoxicity, freshwater	CTUe	1,37E+00	1,36E+00	1,10E-02
Land use	Pt	2,50E-01	2,44E-01	5,66E-03
Water use	m3 depriv.	4,98E-02	4,97E-02	6,40E-05
Resource use, fossils	MJ	2,78E+00	2,78E+00	3,91E-03
Resource use, minerals and metals	kg Sb eq	1,21E-06	1,21E-06	9,04E-10

**Weighted results**

- Normalised and **weighted** results




Figure 7: Normalised and weighted results - PRODUCT 02 – Salad MDD, PET Tray



Funded by  
the European Union

This project has received funding from the European Union’s Horizon Europe Research and Innovation programme under Grant Agreement No 101060806. This document reflects the views of the author(s) and does not necessarily reflect the views or policy of the European Commission. Whilst efforts have been made to ensure the accuracy and completeness of this document, the European Commission shall not be liable for any errors or omissions, however

**Single score**

- Weighted results as single score in  $\mu\text{Pt}$  for all the life cycle stages (Pre-processing and manufacturing: 02. Salad MDD\_PET Tray – PP+M; End-of-Life: 02. Salad MDD\_PET Tray – EoL).
- For product 02 – Salad MDD, PET Tray, the most relevant life cycle stage is PP+M (93,6%). The most relevant processes (processes details are shown in table A2) are related to component 2.2 PET Bowl and are Polyethylene terephthalate pre-processing and manufacturing.




Figure 8: Weighted results as single score in  $\mu\text{Pt}$  - PRODUCT 02 – Salad MDD, PET Tray



**PRODUCT 03 – Sour cream, Cup**

**Characterised results**

- **Characterised** results of all EF impact categories

Tab 6. Characterised results PRODUCT 03 – Sour cream, Cup

Impact category	Unit	Total	03. Sour cream_Cup – PP+M	03. Sour cream_Cup – EoL
Climate change	kg CO2 eq	4,98E-02	3,70E-02	1,28E-02
Ozone depletion	kg CFC11 eq	4,97E-08	4,97E-08	2,23E-11
Ionising radiation	kBq U-235 eq	1,15E-02	1,14E-02	8,99E-06
Photochemical ozone formation	kg NMVOC eq	1,16E-04	1,12E-04	3,07E-06
Particulate matter	disease inc.	2,10E-09	2,08E-09	2,15E-11
Human toxicity, non-cancer	CTUh	4,02E-10	3,85E-10	1,68E-11
Human toxicity, cancer	CTUh	2,66E-11	2,47E-11	1,88E-12
Acidification	mol H+ eq	1,52E-04	1,50E-04	2,19E-06
Eutrophication, freshwater	kg P eq	6,88E-06	6,86E-06	2,58E-08
Eutrophication, marine	kg N eq	3,21E-05	2,79E-05	4,23E-06
Eutrophication, terrestrial	mol N eq	2,91E-04	2,79E-04	1,12E-05
Ecotoxicity, freshwater	CTUe	4,35E-01	4,25E-01	9,99E-03
Land use	Pt	6,78E-02	6,54E-02	2,37E-03
Water use	m3 depriv.	1,95E-02	1,94E-02	3,03E-05
Resource use, fossils	MJ	1,16E+00	1,16E+00	1,60E-03
Resource use, minerals and metals	kg Sb eq	3,30E-07	3,30E-07	4,11E-10

**Weighted results**

- Normalised and **weighted** results




Figure 9: Normalised and weighted results - PRODUCT 03 – Sour cream, Cup



**Funded by  
the European Union**

This project has received funding from the European Union's Horizon Europe Research and Innovation programme under Grant Agreement No 101060806. This document reflects the views of the author(s) and does not necessarily reflect the views or policy of the European Commission. Whilst efforts have been made to ensure the accuracy and completeness of this document, the European Commission shall not be liable for any errors or omissions, however

**Single score**

- Weighted results as single score in  $\mu\text{Pt}$  for all the life cycle stages (Pre-processing and manufacturing: 03. Sour cream\_Cup – PP+M; End-of-Life: 03. Sour cream\_Cup – EoL).
- For product 03 – Sour cream, Cup, the most relevant life cycle stage is PP+M (92,2%). The most relevant processes (processes details are shown in table A3) are related to component 3.3 PP Bowl and are Polypropylene pre-processing and manufacturing.




Figure 10: Weighted results as single score in  $\mu\text{Pt}$  - PRODUCT 03 – Sour cream, Cup



**PRODUCT 04 – Greek yoghurt, Cup**

**Characterised results**

- **Characterised** results of all EF impact categories

Tab 7. Characterised results PRODUCT 04 – Greek yoghurt, Cup

Impact category	Unit	Total	04. Greek yoghurt_Cup – PP+M	04. Greek yoghurt_Cup – EoL
Climate change	kg CO2 eq	8,12E-02	6,01E-02	2,11E-02
Ozone depletion	kg CFC11 eq	8,30E-08	8,30E-08	3,64E-11
Ionising radiation	kBq U-235 eq	1,88E-02	1,88E-02	1,47E-05
Photochemical ozone formation	kg NMVOC eq	1,88E-04	1,83E-04	5,04E-06
Particulate matter	disease inc.	3,34E-09	3,30E-09	3,51E-11
Human toxicity, non-cancer	CTUh	6,44E-10	6,16E-10	2,76E-11
Human toxicity, cancer	CTUh	4,23E-11	3,92E-11	3,08E-12
Acidification	mol H+ eq	2,46E-04	2,42E-04	3,60E-06
Eutrophication, freshwater	kg P eq	1,11E-05	1,10E-05	4,10E-08
Eutrophication, marine	kg N eq	5,21E-05	4,51E-05	6,98E-06
Eutrophication, terrestrial	mol N eq	4,70E-04	4,52E-04	1,84E-05
Ecotoxicity, freshwater	CTUe	6,96E-01	6,80E-01	1,56E-02
Land use	Pt	1,10E-01	1,06E-01	3,88E-03
Water use	m3 depriv.	3,19E-02	3,18E-02	4,93E-05
Resource use, fossils	MJ	1,90E+00	1,90E+00	2,61E-03
Resource use, minerals and metals	kg Sb eq	5,36E-07	5,35E-07	6,71E-10

**Weighted results**

- Normalised and **weighted** results




Figure 11: Normalised and weighted results - PRODUCT 04 – Greek yoghurt, Cup



**Funded by  
the European Union**

This project has received funding from the European Union's Horizon Europe Research and Innovation programme under Grant Agreement No 101060806. This document reflects the views of the author(s) and does not necessarily reflect the views or policy of the European Commission. Whilst efforts have been made to ensure the accuracy and completeness of this document, the European Commission shall not be liable for any errors or omissions, however

**Single score**

- Weighted results as single score in  $\mu\text{Pt}$  for all the life cycle stages (Pre-processing and manufacturing: 04. Greek yoghurt\_Cup - PP+M; End-of-Life: 04. Greek yoghurt\_Cup - EoL).
- For product 04 - Greek yoghurt, Cup, the most relevant life cycle stage is PP+M (92,1%). The most relevant processes (processes details are shown in table A4) are related to component 4.3 PP Bowl and are Polypropylene pre-processing and manufacturing.




Figure 12: Weighted results as single score in  $\mu\text{Pt}$  - PRODUCT 04 - Greek yoghurt, Cup



**Funded by  
the European Union**

This project has received funding from the European Union's Horizon Europe Research and Innovation programme under Grant Agreement No 101060806. This document reflects the views of the author(s) and does not necessarily reflect the views or policy of the European Commission. Whilst efforts have been made to ensure the accuracy and completeness of this document, the European Commission shall not be liable for any errors or omissions, however



## PRODUCT 05 – Pork chop, Wrapped Tray

### Characterised results

- **Characterised** results of all EF impact categories

Tab 8. Characterised results PRODUCT 05 – Pork chop, Wrapped Tray

Impact category	Unit	Total	05. Pork chop_Wrapped Tray – PP+M	05. Pork chop_Wrapped Tray – EoL
Climate change	kg CO2 eq	7,40E-02	5,54E-02	1,86E-02
Ozone depletion	kg CFC11 eq	4,87E-09	4,38E-09	4,97E-10
Ionising radiation	kBq U-235 eq	1,59E-02	1,57E-02	1,17E-04
Photochemical ozone formation	kg NMVOC eq	2,84E-04	2,78E-04	5,89E-06
Particulate matter	disease inc.	2,22E-09	2,16E-09	6,06E-11
Human toxicity, non-cancer	CTUh	3,40E-10	2,71E-10	6,90E-11
Human toxicity, cancer	CTUh	1,92E-11	1,59E-11	3,33E-12
Acidification	mol H+ eq	2,13E-04	2,06E-04	6,98E-06
Eutrophication, freshwater	kg P eq	5,12E-06	4,73E-06	3,88E-07
Eutrophication, marine	kg N eq	3,83E-05	3,38E-05	4,53E-06
Eutrophication, terrestrial	mol N eq	3,62E-04	3,41E-04	2,15E-05
Ecotoxicity, freshwater	CTUe	5,40E-01	2,65E-01	2,75E-01
Land use	Pt	7,12E-02	6,53E-02	5,97E-03
Water use	m3 depriv.	4,18E-02	4,09E-02	8,12E-04
Resource use, fossils	MJ	1,47E+00	1,46E+00	1,20E-02
Resource use, minerals and metals	kg Sb eq	1,51E-07	1,39E-07	1,14E-08

### Weighted results

- Normalised and **weighted** results




Figure 13: Normalised and weighted results - PRODUCT 05 – Pork chop, Wrapped Tray



**Single score**

- Weighted results as single score in  $\mu\text{Pt}$  for all the life cycle stages (Pre-processing and manufacturing: 05. Pork chop\_Wrapped Tray – PP+M; End-of-Life: 05. Pork chop\_Wrapped Tray – EoL).
- For product 05 – Pork chop, Wrapped Tray, the most relevant life cycle stage is PP+M (88,2%). The most relevant processes (processes details are shown in table A5) are related to component 5.2 PSE Tray and are Expandable Polystyrene pre-processing and manufacturing.




Figure 14: Weighted results as single score in  $\mu\text{Pt}$  - PRODUCT 05 – Pork chop, Wrapped Tray



**Funded by  
the European Union**

This project has received funding from the European Union's Horizon Europe Research and Innovation programme under Grant Agreement No 101060806. This document reflects the views of the author(s) and does not necessarily reflect the views or policy of the European Commission. Whilst efforts have been made to ensure the accuracy and completeness of this document, the European Commission shall not be liable for any errors or omissions, however

**PRODUCT 08 – Grated cheese, OPA & LDPE Film**

**Characterised results**

- **Characterised** results of all EF impact categories

Tab 9. Characterised results PRODUCT 08 – Grated cheese, OPA & LDPE Film

Impact category	Unit	Total	08. Grated cheese OPA&LDPE Film – PP+M	08. Grated cheese OPA&LDPE Film – EoL
Climate change	kg CO2 eq	3,33E-02	2,68E-02	6,44E-03
Ozone depletion	kg CFC11 eq	5,73E-08	5,73E-08	1,18E-11
Ionising radiation	kBq U-235 eq	3,17E-03	3,17E-03	4,05E-06
Photochemical ozone formation	kg NMVOC eq	8,33E-05	8,19E-05	1,42E-06
Particulate matter	disease inc.	1,15E-09	1,14E-09	9,31E-12
Human toxicity, non-cancer	CTUh	2,91E-10	2,84E-10	7,52E-12
Human toxicity, cancer	CTUh	1,52E-11	1,44E-11	8,66E-13
Acidification	mol H+ eq	1,04E-04	1,03E-04	1,01E-06
Eutrophication, freshwater	kg P eq	3,11E-06	3,09E-06	1,44E-08
Eutrophication, marine	kg N eq	2,45E-05	2,26E-05	1,89E-06
Eutrophication, terrestrial	mol N eq	2,22E-04	2,17E-04	4,98E-06
Ecotoxicity, freshwater	CTUe	1,25E-01	1,20E-01	4,99E-03
Land use	Pt	6,55E-02	6,45E-02	1,01E-03
Water use	m3 depriv.	1,05E-02	1,05E-02	2,53E-05
Resource use, fossils	MJ	4,94E-01	4,93E-01	8,47E-04
Resource use, minerals and metals	kg Sb eq	1,91E-07	1,91E-07	2,56E-10

**Weighted results**

- Normalised and **weighted** results




Figure 15: Normalised and weighted results - PRODUCT 08 – Grated cheese, OPA & LDPE Film



**Funded by the European Union**

This project has received funding from the European Union’s Horizon Europe Research and Innovation programme under Grant Agreement No 101060806. This document reflects the views of the author(s) and does not necessarily reflect the views or policy of the European Commission. Whilst efforts have been made to ensure the accuracy and completeness of this document, the European Commission shall not be liable for any errors or omissions, however

**Single score**

- Weighted results as single score in  $\mu\text{Pt}$  for all the life cycle stages (Pre-processing and manufacturing: 08. Grated cheese\_OPA&LDPE Film – PP+M; End-of-Life: 08. Grated cheese\_OPA&LDPE Film – EoL).
- For product 08. Grated cheese\_OPA&LDPE Film, the most relevant life cycle stage is PP+M (92,8%). The most relevant processes (processes details are shown in table A8) are related to component 8.3 LDPE Foil and are Polyethylene terephthalate pre-processing and manufacturing.




Figure 16: Weighted results as single score in  $\mu\text{Pt}$  - PRODUCT 08 – Grated cheese, OPA & LDPE Film



**Funded by  
the European Union**

This project has received funding from the European Union's Horizon Europe Research and Innovation programme under Grant Agreement No 101060806. This document reflects the views of the author(s) and does not necessarily reflect the views or policy of the European Commission. Whilst efforts have been made to ensure the accuracy and completeness of this document, the European Commission shall not be liable for any errors or omissions, however

**PRODUCT 09 – Peanut curl, OPP Film**

**Characterised results**

- **Characterised** results of all EF impact categories

Tab 10. Characterised results PRODUCT 09 – Peanut curl, OPP Film

Impact category	Unit	Total	09. Peanut curl_OPP Film – PP+M	09. Peanut curl_OPP Film – EoL
Climate change	kg CO2 eq	2,13E-02	1,49E-02	6,41E-03
Ozone depletion	kg CFC11 eq	1,00E-09	9,99E-10	3,43E-12
Ionising radiation	kBq U-235 eq	3,60E-03	3,60E-03	2,12E-06
Photochemical ozone formation	kg NMVOC eq	4,79E-05	4,66E-05	1,36E-06
Particulate matter	disease inc.	6,45E-10	6,36E-10	9,04E-12
Human toxicity, non-cancer	CTUh	2,60E-10	2,54E-10	6,05E-12
Human toxicity, cancer	CTUh	1,91E-11	1,83E-11	8,56E-13
Acidification	mol H+ eq	5,32E-05	5,23E-05	8,98E-07
Eutrophication, freshwater	kg P eq	1,98E-06	1,97E-06	7,71E-09
Eutrophication, marine	kg N eq	1,35E-05	1,24E-05	1,04E-06
Eutrophication, terrestrial	mol N eq	1,06E-04	1,02E-04	4,66E-06
Ecotoxicity, freshwater	CTUe	1,49E-01	1,48E-01	1,31E-03
Land use	Pt	7,55E-02	7,44E-02	1,04E-03
Water use	m3 depriv.	9,84E-03	9,83E-03	1,15E-05
Resource use, fossils	MJ	5,00E-01	5,00E-01	6,78E-04
Resource use, minerals and metals	kg Sb eq	7,23E-08	7,21E-08	1,22E-10

**Weighted results**

- Normalised and **weighted** results




Figure 17: Normalised and weighted results - PRODUCT 09 – Peanut curl, OPP Film



**Funded by the European Union**

This project has received funding from the European Union’s Horizon Europe Research and Innovation programme under Grant Agreement No 101060806. This document reflects the views of the author(s) and does not necessarily reflect the views or policy of the European Commission. Whilst efforts have been made to ensure the accuracy and completeness of this document, the European Commission shall not be liable for any errors or omissions, however

**Single score**

- Weighted results as single score in  $\mu\text{Pt}$  for all the life cycle stages (Pre-processing and manufacturing: 09. Peanut curl\_OPP Film – PP+M; End-of-Life: 09. Peanut curl\_OPP Film – EoL).
- For product 09. Peanut curl\_OPP Film, the most relevant life cycle stage is PP+M (90,2%). The most relevant processes (processes details are shown in table A9 are related to component 9.2 OPP Film and are Polypropylene pre-processing and manufacturing.




Figure 18: Weighted results as single score in  $\mu\text{Pt}$  - PRODUCT 09 – Peanut curl, OPP Film



**Funded by  
the European Union**

This project has received funding from the European Union's Horizon Europe Research and Innovation programme under Grant Agreement No 101060806. This document reflects the views of the author(s) and does not necessarily reflect the views or policy of the European Commission. Whilst efforts have been made to ensure the accuracy and completeness of this document, the European Commission shall not be liable for any errors or omissions, however

**PRODUCT 10 – Savory biscuits, OPP & Cardboard**

**Characterised results**

- **Characterised** results of all EF impact categories

Tab 11. Characterised results PRODUCT 10 – Savory biscuits, OPP & Cardboard

Impact category	Unit	Total	10. Savory biscuits OPP&Cardboard – PP+M	10. Savory biscuits OPP&Cardboard – EoL
Climate change	kg CO2 eq	5,17E-02	4,46E-02	7,05E-03
Ozone depletion	kg CFC11 eq	1,27E-09	1,26E-09	9,16E-12
Ionising radiation	kBq U-235 eq	1,11E-02	1,11E-02	8,36E-06
Photochemical ozone formation	kg NMVOC eq	1,61E-04	1,56E-04	4,27E-06
Particulate matter	disease inc.	5,38E-09	5,33E-09	5,32E-11
Human toxicity, non-cancer	CTUh	7,71E-10	7,41E-10	3,00E-11
Human toxicity, cancer	CTUh	2,53E-11	2,40E-11	1,27E-12
Acidification	mol H+ eq	2,31E-04	2,29E-04	2,53E-06
Eutrophication, freshwater	kg P eq	1,88E-05	1,87E-05	3,94E-08
Eutrophication, marine	kg N eq	5,85E-05	5,27E-05	5,81E-06
Eutrophication, terrestrial	mol N eq	5,03E-04	4,93E-04	9,98E-06
Ecotoxicity, freshwater	CTUe	2,49E-01	2,28E-01	2,06E-02
Land use	Pt	2,64E+00	2,64E+00	3,02E-03
Water use	m3 depriv.	1,93E-02	1,91E-02	1,85E-04
Resource use, fossils	MJ	7,89E-01	7,86E-01	3,19E-03
Resource use, minerals and metals	kg Sb eq	1,53E-07	1,52E-07	7,11E-10

**Weighted results**

- Normalised and **weighted** results




Figure 19: Normalised and weighted results - PRODUCT 10 – Savory biscuits, OPP & Cardboard



**Funded by  
the European Union**

This project has received funding from the European Union's Horizon Europe Research and Innovation programme under Grant Agreement No 101060806. This document reflects the views of the author(s) and does not necessarily reflect the views or policy of the European Commission. Whilst efforts have been made to ensure the accuracy and completeness of this document, the European Commission shall not be liable for any errors or omissions, however

**Single score**

- Weighted results as single score in  $\mu$ Pt for all the life cycle stages (Pre-processing and manufacturing: 10. Savory bisc\_ OPP&Cardboard – PP+M; End-of-Life: 10. Savory bisc\_ OPP&Cardboard – EoL).
- For product 10. Savory bisc\_ OPP&Cardboard, the most relevant life cycle stage is PP+M (95,4%). The most relevant processes (processes details are shown in table A10) are related to component 10.1 Cardboard Box and are Folding boxboard carton pre-processing and manufacturing.




Figure 20: Weighted results as single score in  $\mu$ Pt - PRODUCT 10 – Savory biscuits, OPP & Cardboard



Funded by  
the European Union

This project has received funding from the European Union's Horizon Europe Research and Innovation programme under Grant Agreement No 101060806. This document reflects the views of the author(s) and does not necessarily reflect the views or policy of the European Commission. Whilst efforts have been made to ensure the accuracy and completeness of this document, the European Commission shall not be liable for any errors or omissions, however



## PRODUCT 11 – Orange Juice\_PET clear Bottle

### Characterised results

- **Characterised** results of all EF impact categories

Tab 12. Characterised results PRODUCT 11 – Orange Juice\_PET clear Bottle

Impact category	Unit	Total	11. Orange Juice_PET clear Bottle – PP+M	11. Orange Juice_PET clear Bottle – EoL
Climate change	kg CO2 eq	1,11E-01	8,03E-02	3,11E-02
Ozone depletion	kg CFC11 eq	2,16E-07	2,16E-07	1,63E-11
Ionising radiation	kBq U-235 eq	6,86E-02	6,86E-02	1,48E-05
Photochemical ozone formation	kg NMVOC eq	2,75E-04	2,65E-04	9,89E-06
Particulate matter	disease inc.	3,24E-09	3,19E-09	5,55E-11
Human toxicity, non-cancer	CTUh	1,22E-09	1,21E-09	1,07E-11
Human toxicity, cancer	CTUh	4,40E-11	3,98E-11	4,19E-12
Acidification	mol H+ eq	3,05E-04	2,98E-04	6,84E-06
Eutrophication, freshwater	kg P eq	1,42E-05	1,42E-05	4,01E-08
Eutrophication, marine	kg N eq	8,72E-05	6,45E-05	2,26E-05
Eutrophication, terrestrial	mol N eq	6,55E-04	6,19E-04	3,65E-05
Ecotoxicity, freshwater	CTUe	3,55E-01	3,45E-01	9,65E-03
Land use	Pt	5,50E-01	5,44E-01	5,91E-03
Water use	m3 depriv.	-3,72E-02	-3,73E-02	6,39E-05
Resource use, fossils	MJ	3,02E+00	3,02E+00	4,17E-03
Resource use, minerals and metals	kg Sb eq	5,46E-06	5,46E-06	6,73E-10

### Weighted results

- Normalised and **weighted** results




Figure 21: Normalised and weighted results - PRODUCT 11 – Orange Juice\_PET clear Bottle



Funded by  
the European Union

This project has received funding from the European Union's Horizon Europe Research and Innovation programme under Grant Agreement No 101060806. This document reflects the views of the author(s) and does not necessarily reflect the views or policy of the European Commission. Whilst efforts have been made to ensure the accuracy and completeness of this document, the European Commission shall not be liable for any errors or omissions, however

**Single score**

- Weighted results as single score in  $\mu\text{Pt}$  for all the life cycle stages (Pre-processing and manufacturing: 11. Orange Juice\_PET clear Bottle – PP+M; End-of-Life: 11. Orange Juice\_PET clear Bottle – EoL)
- For product 11. Orange Juice\_PET clear Bottle, the most relevant life cycle stage is PP+M (94,4%). The most relevant processes (processes details are shown in table A11) are related to component 11.3 PET Bottle and are Polyethylene terephthalate pre-processing and manufacturing.




Figure 22: Weighted results as single score in  $\mu\text{Pt}$  - PRODUCT 11 – Orange Juice\_PET clear Bottle



**PRODUCT 12 – UHT Milk\_PET opaque Bottle**

**Characterised results**

- **Characterised** results of all EF impact categories

Tab 13. Characterised results PRODUCT 12 – UHT Milk\_PET opaque Bottle

Impact category	Unit	Total	12. UHT Milk_PET opaque Bottle – PP+M	12. UHT Milk_PET opaque Bottle – EoL
Climate change	kg CO2 eq	9,76E-02	7,02E-02	2,74E-02
Ozone depletion	kg CFC11 eq	1,85E-07	1,85E-07	1,43E-11
Ionising radiation	kBq U-235 eq	5,93E-02	5,93E-02	1,29E-05
Photochemical ozone formation	kg NMVOC eq	2,40E-04	2,32E-04	8,61E-06
Particulate matter	disease inc.	2,83E-09	2,78E-09	4,85E-11
Human toxicity, non-cancer	CTUh	1,05E-09	1,04E-09	9,70E-12
Human toxicity, cancer	CTUh	3,82E-11	3,45E-11	3,68E-12
Acidification	mol H+ eq	2,66E-04	2,60E-04	5,96E-06
Eutrophication, freshwater	kg P eq	1,23E-05	1,23E-05	3,52E-08
Eutrophication, marine	kg N eq	7,57E-05	5,62E-05	1,95E-05
Eutrophication, terrestrial	mol N eq	5,71E-04	5,40E-04	3,17E-05
Ecotoxicity, freshwater	CTUe	3,07E-01	2,98E-01	8,43E-03
Land use	Pt	4,76E-01	4,71E-01	5,17E-03
Water use	m3 depriv.	-3,12E-02	-3,12E-02	5,60E-05
Resource use, fossils	MJ	2,64E+00	2,64E+00	3,65E-03
Resource use, minerals and metals	kg Sb eq	4,68E-06	4,68E-06	5,90E-10

**Weighted results**

- Normalised and **weighted** results




Figure 23: Normalised and weighted results – PRODUCT 12 – UHT Milk\_PET opaque Bottle



**Funded by  
the European Union**

This project has received funding from the European Union’s Horizon Europe Research and Innovation programme under Grant Agreement No 101060806. This document reflects the views of the author(s) and does not necessarily reflect the views or policy of the European Commission. Whilst efforts have been made to ensure the accuracy and completeness of this document, the European Commission shall not be liable for any errors or omissions, however

**Single score**

- Weighted results as single score in  $\mu$ Pt for all the life cycle stages (Pre-processing and manufacturing: 12. UHT Milk\_PET opaque Bottle – PP+M; End-of-Life: 12. UHT Milk\_PET opaque Bottle – EoL)
- For product 12. UHT Milk\_PET opaque Bottle, the most relevant life cycle stage is PP+M (94,3%). The most relevant processes (processes details are shown in table A12) are related to component 12.3 PET Bottle and are Polyethylene terephthalate pre-processing and manufacturing.




Figure 24: Weighted results as single score in  $\mu$ Pt - PRODUCT 12 – UHT Milk\_PET opaque Bottle



Funded by  
the European Union

This project has received funding from the European Union's Horizon Europe Research and Innovation programme under Grant Agreement No 101060806. This document reflects the views of the author(s) and does not necessarily reflect the views or policy of the European Commission. Whilst efforts have been made to ensure the accuracy and completeness of this document, the European Commission shall not be liable for any errors or omissions, however

**PRODUCT 13 – UHT Milk\_PEHD Bottle**

**Characterised results**

- **Characterised** results of all EF impact categories

Tab 14. Characterised results PRODUCT 13 – UHT Milk\_PEHD Bottle

Impact category	Unit	Total	13. UHT Milk_PEHD Bottle – PP+M	13. UHT Milk_PEHD Bottle – EoL
Climate change	kg CO2 eq	1,38E-01	8,95E-02	4,86E-02
Ozone depletion	kg CFC11 eq	1,48E-09	1,45E-09	2,49E-11
Ionising radiation	kBq U-235 eq	6,73E-02	6,73E-02	1,45E-05
Photochemical ozone formation	kg NMVOC eq	3,09E-04	3,00E-04	8,90E-06
Particulate matter	disease inc.	3,46E-09	3,40E-09	5,86E-11
Human toxicity, non-cancer	CTUh	7,03E-10	6,58E-10	4,47E-11
Human toxicity, cancer	CTUh	3,26E-11	2,69E-11	5,66E-12
Acidification	mol H+ eq	3,15E-04	3,09E-04	5,89E-06
Eutrophication, freshwater	kg P eq	1,22E-05	1,21E-05	5,32E-08
Eutrophication, marine	kg N eq	7,06E-05	6,31E-05	7,50E-06
Eutrophication, terrestrial	mol N eq	6,49E-04	6,18E-04	3,05E-05
Ecotoxicity, freshwater	CTUe	1,51E-01	1,41E-01	9,69E-03
Land use	Pt	3,81E-01	3,75E-01	6,74E-03
Water use	m3 depriv.	-1,09E-02	-1,10E-02	7,94E-05
Resource use, fossils	MJ	4,06E+00	4,06E+00	4,47E-03
Resource use, minerals and metals	kg Sb eq	4,25E-07	4,24E-07	8,42E-10

**Weighted results**

- Normalised and **weighted** results




Figure 25: Normalised and weighted results - PRODUCT 13 – UHT Milk\_PEHD Bottle



**Funded by  
the European Union**

This project has received funding from the European Union's Horizon Europe Research and Innovation programme under Grant Agreement No 101060806. This document reflects the views of the author(s) and does not necessarily reflect the views or policy of the European Commission. Whilst efforts have been made to ensure the accuracy and completeness of this document, the European Commission shall not be liable for any errors or omissions, however

**Single score**

- Weighted results as single score in  $\mu\text{Pt}$  for all the life cycle stages (Pre-processing and manufacturing: 13. UHT Milk\_PEHD Bottle – PP+M; End-of-Life: 13. UHT Milk\_PEHD Bottle – EoL)
- For product 13 – UHT Milk\_PEHD Bottle, the most relevant life cycle stage is PP+M (88,8%). The most relevant processes (processes details are shown in table A13) are related to component 13.2 Bottle and are Polyethylene pre-processing and manufacturing.
- 




Figure 26: Weighted results as single score in  $\mu\text{Pt}$  - PRODUCT 13 – UHT Milk\_PEHD Bottle



Funded by the European Union

This project has received funding from the European Union's Horizon Europe Research and Innovation programme under Grant Agreement No 101060806. This document reflects the views of the author(s) and does not necessarily reflect the views or policy of the European Commission. Whilst efforts have been made to ensure the accuracy and completeness of this document, the European Commission shall not be liable for any errors or omissions, however

## PRODUCT 14 – Savory bisc\_BOPP&Cardboard

### Characterised results

- **Characterised** results of all EF impact categories

Tab 15. Characterised results PRODUCT 14 – Savory bisc\_BOPP&Cardboard

Impact category	Unit	Total	14. Savory bisc_BOPP&Cardboard – PP+M	14. Savory bisc_BOPP&Cardboard – EoL
Climate change	kg CO2 eq	6,06E-02	5,24E-02	8,21E-03
Ozone depletion	kg CFC11 eq	1,44E-09	1,43E-09	1,07E-11
Ionising radiation	kBq U-235 eq	1,23E-02	1,22E-02	9,74E-06
Photochemical ozone formation	kg NMVOC eq	1,88E-04	1,83E-04	4,97E-06
Particulate matter	disease inc.	6,14E-09	6,08E-09	6,20E-11
Human toxicity, non-cancer	CTUh	8,81E-10	8,46E-10	3,50E-11
Human toxicity, cancer	CTUh	2,90E-11	2,75E-11	1,48E-12
Acidification	mol H+ eq	2,67E-04	2,65E-04	2,95E-06
Eutrophication, freshwater	kg P eq	2,13E-05	2,13E-05	4,59E-08
Eutrophication, marine	kg N eq	6,73E-05	6,06E-05	6,77E-06
Eutrophication, terrestrial	mol N eq	5,80E-04	5,68E-04	1,16E-05
Ecotoxicity, freshwater	CTUe	2,83E-01	2,59E-01	2,40E-02
Land use	Pt	2,99E+00	2,98E+00	3,52E-03
Water use	m3 depriv.	2,33E-02	2,30E-02	2,15E-04
Resource use, fossils	MJ	9,62E-01	9,59E-01	3,71E-03
Resource use, minerals and metals	kg Sb eq	1,79E-07	1,79E-07	8,28E-10

### Weighted results

- Normalised and **weighted** results




Figure 27: Normalised and weighted results - PRODUCT 14 – Savory bisc\_BOPP&Cardboard



Funded by  
the European Union

This project has received funding from the European Union's Horizon Europe Research and Innovation programme under Grant Agreement No 101060806. This document reflects the views of the author(s) and does not necessarily reflect the views or policy of the European Commission. Whilst efforts have been made to ensure the accuracy and completeness of this document, the European Commission shall not be liable for any errors or omissions, however

**Single score**

- Weighted results as single score in  $\mu\text{Pt}$  for all the life cycle stages (Pre-processing and manufacturing: 14. Savory bisc\_BOPP&Cardboard – PP+M; End-of-Life: 14. Savory bisc\_BOPP&Cardboard – EoL)
- For product 14 – Savory bisc\_BOPP&Cardboard, the most relevant life cycle stage is PP+M (95,4%). The most relevant processes (processes details are shown in table A14) are related to component 14.1 Cardboard Box and are Folding boxboard carton pre-processing and manufacturing




Figure 28: Weighted results as single score in  $\mu\text{Pt}$  - PRODUCT 14 – Savory bisc\_BOPP&Cardboard



**Funded by  
the European Union**

This project has received funding from the European Union's Horizon Europe Research and Innovation programme under Grant Agreement No 101060806. This document reflects the views of the author(s) and does not necessarily reflect the views or policy of the European Commission. Whilst efforts have been made to ensure the accuracy and completeness of this document, the European Commission shall not be liable for any errors or omissions, however



## 7. INTERPRETING PEF RESULTS

### 7.1. Relevant impact categories

In the previous section, characterized, normalised and weighted results for each EF impact category have been presented together with the single score for each life cycle stage. In this paragraph, the most relevant impact categories will be highlighted. As prescribed in the PEF method, impact categories cumulatively contributing at least 80% of the total environmental impact will be identified for each product based on the normalised and weighted results.

Below, for each product, a table is provided in which most relevant impact categories are ranked in descending order of impact on the total life cycle.

#### PRODUCT 01 – Florette Shaker, PET Cup

Tab 16. Most relevant impact categories PRODUCT 01 – Florette Shaker, PET Cup

<b>Label</b>	<b>Total (µPt)</b>	<b>%</b>
Resource use, fossils	1.46	27.9%
Climate change	1.41	26.9%
Resource use, minerals and metals	0.59	11.3%
Particulate matter	0.26	5.0%
Ecotoxicity, freshwater	0.25	4.9%
Ozone depletion	0.24	4.5%
<b>Sum</b>		<b>80.5%</b>

#### PRODUCT 02 – Salad MDD, PET Tray

Tab 17. Most relevant impact categories - PRODUCT 02 – Salad MDD, PET Tray

<b>Label</b>	<b>Total (µPt)</b>	<b>%</b>
Resource use, fossils	3.56	28.0%
Climate change	3.41	26.9%
Resource use, minerals and metals	1.43	11.3%
Particulate matter	0.63	5.0%
Ecotoxicity, freshwater	0.62	4.9%
Ozone depletion	0.57	4.5%
<b>Sum</b>		<b>80.4%</b>

#### PRODUCT 03 – Sour cream, Cup

Tab 18. Most relevant impact categories - PRODUCT 03 – Sour cream, Cup

<b>Label</b>	<b>Total (µPt)</b>	<b>%</b>
Resource use, fossils	1.48	32.1%
Climate change	1.30	28.0%
Resource use, minerals and metals	0.39	8.5%
Particulate matter	0.32	6.8%
Ecotoxicity, freshwater	0.20	4.2%
<b>Sum</b>		<b>79.6%</b>



## PRODUCT 04 – Greek yoghurt, Cup

Tab 19. Most relevant impact categories - PRODUCT 04 – Greek yoghurt, Cup

<b>Label</b>	<b>Total (μPt)</b>	<b>%</b>
Resource use, fossils	2.43	32.3%
Climate change	2.11	28.0%
Resource use, minerals and metals	0.64	8.4%
Particulate matter	0.50	6.7%
Ecotoxicity, freshwater	0.31	4.2%
<b>Sum</b>		<b>79.6%</b>

## PRODUCT 05 – Pork chop, Wrapped Tray

Tab 20. Most relevant impact categories - PRODUCT 05 – Pork chop, Wrapped Tray

<b>Label</b>	<b>Total (μPt)</b>	<b>%</b>
Climate change	1.92	32.5%
Resource use, fossils	1.89	31.8%
Photochemical ozone formation	0.33	5.6%
Particulate matter	0.33	5.6%
Water use	0.31	5.2%
<b>Sum</b>		<b>80.8%</b>

## PRODUCT 08 – Grated cheese, OPA & LDPE Film

Tab 21. Most relevant impact categories - PRODUCT 07 – Grated cheese, OPA & LDPE Film

<b>Label</b>	<b>Total (μPt)</b>	<b>%</b>
Climate change	0.86	34.1%
Resource use, fossils	0.63	24.9%
Resource use, minerals and metals	0.23	8.9%
Particulate matter	0.17	6.8%
Acidification	0.12	4.6%
<b>Sum</b>		<b>79.3%</b>

## PRODUCT 09 – Peanut curl, OPP Film

Tab 22. Most relevant impact categories - PRODUCT 09 – Peanut curl, OPP Film

<b>Label</b>	<b>Total (μPt)</b>	<b>%</b>
Resource use, fossils	0.64	35.5%
Climate change	0.55	30.6%
Particulate matter	0.10	5.4%
Resource use, minerals and metals	0.09	4.7%
Water use	0.07	4.0%
<b>Sum</b>		<b>80.3%</b>



**PRODUCT 10 – Savory biscuits, OPP & Cardboard**
*Tab 23. Most relevant impact categories - PRODUCT 10 – Savory biscuits, OPP & Cardboard*

<b>Label</b>	<b>Total (µPt)</b>	<b>%</b>
Climate change	1.34	26.6%
Resource use, fossils	1.01	20.0%
Particulate matter	0.81	16.0%
Eutrophication, freshwater	0.33	6.5%
Acidification	0.26	5.1%
Land use	0.26	5.1%
<b>Sum</b>		<b>79.3%</b>

**PRODUCT 11 – Orange Juice\_PET clear Bottle**
*Tab 24. Most relevant impact categories - PRODUCT 11 – Orange Juice\_PET clear Bottle*

<b>Label</b>	<b>Total (µPt)</b>	<b>%</b>
Resource use, minerals and metals	6,47	40,3%
Resource use, fossils	3,86	24,1%
Climate change	2,90	18,0%
<b>Sum</b>		<b>82.4%</b>

**PRODUCT 12 – UHT Milk\_PET opaque Bottle**
*Tab 25. Most relevant impact categories - PRODUCT 12 – UHT Milk\_PET opaque Bottle*

<b>Label</b>	<b>Total (µPt)</b>	<b>%</b>
Resource use, minerals and metals	5,56	39,9%
Resource use, fossils	3,38	24,3%
Climate change	2,54	18,2%
<b>Sum</b>		<b>82.4%</b>

**PRODUCT 13 – UHT Milk\_PEHD Bottle**
*Tab 26. Most relevant impact categories - PRODUCT 13 – UHT Milk\_PEHD Bottle*

<b>Label</b>	<b>Total (µPt)</b>	<b>%</b>
Resource use, fossils	5,20	43,7%
Climate change	3,59	30,2%
Ionising radiation	0,80	6,7%
<b>Sum</b>		<b>80.5%</b>



**PRODUCT 14 – Savory bisc\_BOPP & Cardboard**

*Tab 27. Most relevant impact categories - PRODUCT 14 – Savory bisc\_BOPP & Cardboard*

<b>Label</b>	<b>Total (µPt)</b>	<b>%</b>
<i>Climate change</i>	1,58	26,7%
<i>Resource use, fossils</i>	1,23	20,9%
<i>Particulate matter</i>	0,92	15,7%
<i>Eutrophication, freshwater</i>	0,37	6,3%
<i>Acidification</i>	0,30	5,1%
<i>Land use</i>	0,29	4,9%
<b>Sum</b>		<b>79,5%</b>

## 7.2. Relevant impact categories overview and comments

### IMPACT CATEGORIES OVERVIEW

The graphic below (Fig.29) groups the impacts of all the products into the consistent impact categories, presented as percentage contribution (Tab. 16-27).






Figure 29: Impact categories relevant contributions on overall products.



Funded by the European Union

This project has received funding from the European Union's Horizon Europe Research and Innovation programme under Grant Agreement No 101060806. This document reflects the views of the author(s) and does not necessarily reflect the views or policy of the European Commission. Whilst efforts have been made to ensure the accuracy and completeness of this document, the European Commission shall not be liable for any errors or omissions, however

From this graphic it is possible to highlight that, for all 12 products analysed, the two most relevant impact categories are climate change and fossil resources use. These results mainly derive from the extensive use of fossil-based polymeric materials in the manufacturing of the analysed packaging.

In the end-of-life phase, the incineration and landfill processes, whose impact is included in the calculation, strongly impact climate change.

The relative differences among the products, within the same impact categories, are mainly due to the type of constituent polymeric materials and the impact of their production process.



**Funded by  
the European Union**

This project has received funding from the European Union's Horizon Europe Research and Innovation programme under Grant Agreement No 101060806. This document reflects the views of the author(s) and does not necessarily reflect the views or policy of the European Commission. Whilst efforts have been made to ensure the accuracy and completeness of this document, the European Commission shall not be liable for any errors or omissions, however

## 8. ANNEXES

### 8.1. Annex I: Data collection

#### PRODUCT 01 – Florette Shaker, PET Cup

Name of the product	<i>Floréale Prepared fruits – PET cup</i>		
Packaging capacity	400 ml		
<b>PRODUCT COMPOSITION - INBOUND OF RAW MATERIALS</b>			
	Commercial name of the product (Material Data Sheet)	Weight	Process technology
		(g)	
<b>PACKAGING BODY</b>			
<i>Shaker PET</i>	Polyethylene terephthalate	11,6	<i>Thermoforming</i>
<i>PET foil lid</i>	Polyethylene terephthalate	0,8	Extrusion
<b>Packaging production technology</b>	<i>Thermoformed shaker</i>	12,4	

Image



**Brief description:**  
Preformed PET shaker, heat sealed with a thin PET foil lid

#### PRODUCT 02 – Salad MDD, PET Tray

Name of the product	<i>LSDH Prepared salad – PET tray</i>		
Packaging capacity	250 g		
<b>PRODUCT COMPOSITION - INBOUND OF RAW MATERIALS</b>			
	Commercial name of the product (Material Data Sheet)	Weight	Process technology
		(g)	
<b>PACKAGING BODY</b>			
<i>{Bowf} Tray 192 mm x 192 x 53</i>	PET	20	<i>thermoforming</i>
<i>Lid</i>	PET	10	<i>thermoforming</i>
		30	
<b>Packaging production technology</b>	<i>Manual filling (in line by operators), chilled</i>		

Image




Funded by  
the European Union

This project has received funding from the European Union's Horizon Europe Research and Innovation programme under Grant Agreement No 101060806. This document reflects the views of the author(s) and does not necessarily reflect the views or policy of the European Commission. Whilst efforts have been made to ensure the accuracy and completeness of this document, the European Commission shall not be liable for any errors or omissions, however

## PRODUCT 03 – Sour cream, Cup

Name of the product	Yoghurt – PP cup		
Packaging capacity	201g		
<b>PRODUCT COMPOSITION - INBOUND OF RAW MATERIALS</b>			
	Commercial name of the product (Material Data Sheet)	Weight	Process technology
		(g)	
<b>PACKAGING BODY</b>			
Cup	PP	8,5	thermoforming
Lid	Aluminium	0,81	
Overcap	PET	3,05	thermoforming
Packaging production technology	Preformed cup	12,36	



## PRODUCT 04 – Greek yoghurt, Cup

Name of the product	Yoghurt – Cup with lid and over		
Packaging capacity	450g		
<b>PRODUCT COMPOSITION - INBOUND OF RAW MATERIALS</b>			
	Commercial name of the product (Material Data Sheet)	Weight	Process technology
		(g)	
<b>PACKAGING BODY</b>			
Cup	PP	14	thermoforming
Lid	Aluminum	1,25	
Overcap	PET	5	thermoforming
Packaging production technology	Preformed cup	20,25	





**PRODUCT 05 – Pork chop, Wrapped Tray**

Name of the product	<i>In shop – PSE Tray</i>		
Packaging capacity	500 g		
<b>PRODUCT COMPOSITION - INBOUND OF RAW MATERIALS</b>			
	Commercial name of the product (Material Data Sheet)	Weight (g)	Process technology
<b>PACKAGING BODY</b>			
<i>Tray (5.2)</i>	EPS	10,9	<i>Sheet extrusion and thermoforming + (foaming)</i>
<i>Wrapping film (5.1)</i>	PVC	2,9	Bubble extrusion
Packaging production technology		13,8	


**PRODUCT 08 – Grated cheese, OPA & LDPE Film**

Name of the product	<i>Entremont (Sodiaal) Cheese – OPA &amp; LDPE film</i>		
Packaging capacity	180g		
<b>PRODUCT COMPOSITION - INBOUND OF RAW MATERIALS</b>			
	Commercial name of the product (Material Data Sheet)	Weight (g)	Process technology
<b>PACKAGING BODY</b>			
<i>Oriented Polyamid (17 g/m<sup>2</sup>)</i>	Oriented Polyamid	1,3	<i>Extrusion</i>
<i>Ink</i>	Ink	0,11	Gravure Printing
<i>Adhesive</i>	Adhesive	0,15	Complexing
<i>Polyethylene (50 g/m<sup>2</sup>)</i>	Polyethylene	3,5	Extrusion
		5,06	
Packaging production technology	<i>Complexing</i>		



**PRODUCT 09 – Peanut curl, OPP Film**

Name of the product	<i>Altho Chips – pouch bag - OPP film</i>		
Packaging capacity	125g		
<b>PRODUCT COMPOSITION - INBOUND OF RAW MATERIALS</b>			
	Commercial name of the product (Material Data Sheet)	Weight (g)	Process technology
<b>PACKAGING BODY</b>			
<i>OPPmat20</i>	<i>Oriented Polypropylene</i>	2,16	<i>Extrusion</i>
<i>Metallization</i>		0,0032	<i>Metallization</i>
<i>Adhesive</i>		0,296	<i>Curing</i>
<i>Printing – Inks</i>		0,414	<i>Flexography / Helioprinting</i>
<i>OPPmet25</i>	<i>Oriented Polypropylene</i>	2,7	<i>Extrusion</i>
<i>Varnish (Optional)</i>			
<b>Packaging production technology</b>	<i>Lamination</i>	5,5732	



**Brief description:** flat film  
size: 395 mm x 300mm  
(grammage 47 g/m2)

**PRODUCT 10 – Savory biscuits, OPP & Cardboard**

Name of the product	<i>Savory biscuits – OPP bags + cardboard</i>		
Packaging capacity	<i>Most common 85g (Min 85g/Max105g)</i>		
<b>PRODUCT COMPOSITION - INBOUND OF RAW MATERIALS</b>			
	Commercial name of the product (Material Data Sheet)	Weight (g)	Process technology
<b>PACKAGING BODY</b>			
<i>Bag (Width 355mm / Length 180mm)</i>	<i>Coex Gloss OPP 15µm</i>	0,798525	<i>Extrusion</i>
<i>Bag (Width 355mm / Length 180mm)</i>	<i>Coex Metallized OPP 15µm</i>	0,792675	
<i>Bag (Width 355mm / Length 180mm)</i>	<i>Metallization</i>	0,0117	
<i>Bag (Width 355mm / Length 180mm)</i>	<i>Adhesive</i>	0,14625	
		1,74915	
<i>Cardboard box</i>	<i>Hermicoat GD2 95% recycled 340gsm</i>	23,51	<i>Flat cut</i>
<i>Cardboard box</i>	<i>Ink</i>	0,11	
<i>Cardboard box</i>	<i>Acrylic varnish</i>	0,34	
<i>Cardboard box</i>	<i>Glue</i>	0,04	
		24,00	
<b>Packaging production technology</b>	<i>Lamination (bag)</i>	25,75	



**Brief description:** 15 OPP/15 OPPmet bags  
One supplier only : India  
No printing on the bag  
Printing on the box :  
Offset printing  
5-6 colors + acrylic varnish



**PRODUCT 11 – Orange Juice\_PET clear Bottle**

<b>Name of the product</b>		<i>LSDH Juice – PET clear bottle 50% recycled</i>	
<b>Packaging capacity</b>		<i>1L</i>	
<b>PRODUCT COMPOSITION - INBOUND OF RAW MATERIALS</b>			
	<b>Commercial name of the product (Material Data Sheet)</b>	<b>Weight</b>	<b>Process technology</b>
		<b>(g)</b>	
<b>PACKAGING BODY</b>			
<i>bottle</i>	<i>PET 50% recycled</i>	<i>28</i>	<i>Injection / blowing</i>
<i>cap</i>	<i>HDPE</i>	<i>3</i>	<i>Injection</i>
<i>label</i>	<i>OPP</i>	<i>1</i>	<i>Extrusion</i>
		<b>Total</b>	<b>32</b>
<b>Packaging production technology</b>	<i>Aseptic filling</i>		



**PRODUCT 12 – UHT Milk\_PET opaque Bottle**

<b>Name of the product</b>		<i>LSDH Milk – PET opaque bottle 50 % recycled</i>	
<b>Packaging capacity</b>		<i>1L</i>	
<b>PRODUCT COMPOSITION - INBOUND OF RAW MATERIALS</b>			
	<b>Commercial name of the product (Material Data Sheet)</b>	<b>Weight</b>	<b>Process technology</b>
		<b>(g)</b>	
<b>PACKAGING BODY</b>			
<i>Bottle</i>	<i>Opaque PET 50% recycled</i>	<i>24</i>	<i>Injection / blowing</i>
<i>Cap</i>	<i>HDPE</i>	<i>3</i>	<i>Injection</i>
<i>label</i>	<i>OPP</i>	<i>1</i>	<i>Extrusion</i>
		<b>Total</b>	<b>28</b>
<b>Packaging production technology</b>	<i>Aseptic filling</i>		



**PRODUCT 13 – UHT Milk\_PEHD Bottle**

<b>Name of the product</b>	<i>Sodiaal Milk – PEHD Bottle</i>		
<b>Packaging capacity</b>	1L		
<b>PRODUCT COMPOSITION - INBOUND OF RAW MATERIALS</b>			
	<b>Commercial name of the product (Material Data Sheet)</b>	<b>Weight</b>	<b>Process technology</b>
		(g)	
<b>PACKAGING BODY</b>			
<i>hdPE + MM White</i>	<i>Inner layer</i>	<i>4,95</i>	<i>Co-extrusion - Soufflage</i>
<i>hdPE + MM Black</i>	<i>Light barrier</i>	<i>16,5</i>	<i>Co-extrusion - Soufflage</i>
<i>hdPE + MM White</i>	<i>Outer layer</i>	<i>11,55</i>	<i>Co-extrusion - Soufflage</i>
<i>hdPE + MM Color</i>	<i>Cap</i>	<i>2,7</i>	<i>injection</i>
		<b>Total</b>	<b>35,7</b>
<b>Packaging production technology</b>	<i>Co-extrusion - Soufflage</i>		


**PRODUCT 14 – Savory bisc\_BOPP & Cardboard**

<b>Name of the product</b>	<i>Savory biscuits – Minis biscuits fourrés chocolat 168g</i>		
<b>Packaging capacity</b>	168g		
<b>PRODUCT COMPOSITION - INBOUND OF RAW MATERIALS</b>			
	<b>Commercial name of the product (Material Data Sheet)</b>	<b>Weight</b>	<b>Process technology</b>
		(g)	
<b>PACKAGING BODY</b>			
<i>Printed foil</i>	<i>White cavitated BOPP coated LTS + inks</i>	<i>2,98</i>	<i>Extrusion + flexo</i>
<i>Cardboard box</i>	<i>GT1 with 95% of recycled material + inks + varnish</i>	<i>27</i>	<i>Offset</i>
	<b>Totale</b>	<b>29,98</b>	
<b>Packaging production technology</b>			



**Brief description:**  
1 cardboard box + 4 flowpacks of 6 biscuits



**Funded by  
the European Union**

This project has received funding from the European Union's Horizon Europe Research and Innovation programme under Grant Agreement No 101060806. This document reflects the views of the author(s) and does not necessarily reflect the views or policy of the European Commission. Whilst efforts have been made to ensure the accuracy and completeness of this document, the European Commission shall not be liable for any errors or omissions, however

## References

COMMISSION RECOMMENDATION (EU) 2021/2279 of 15 December 2021 on the use of the Environmental Footprint methods to measure and communicate the life cycle environmental performance of products and organisations. Available in: <https://eur-lex.europa.eu/legal-content/EN/TXT/HTML/?uri=CELEX:32021H2279>

Wolf, M. A., The Circular Footprint Formula (CFF) and its practical application training. Environmental Footprint (EF) transition phase, 2019. Webinar available in: <https://ec.europa.eu/environment/eusd/videos/2019-10-08%2016.01%20The%20Circular%20Footprint%20Formula.mp4>

Zampori, L. and Pant, R., Suggestions for updating the Product Environmental Footprint (PEF) method, EUR 29682 EN, Publications Office of the European Union, Luxembourg, 2019, ISBN 978-92-76- 00654-1, doi:10.2760/424613, JRC11595. Available in : <https://publications.jrc.ec.europa.eu/repository/handle/JRC115959>

